

EBECRYL® 170

Acidic Acrylate

July 2017



INTRODUCTION

EBECRYL 170 is an acidic acrylate adhesion promoter designed as an additive for ultraviolet (UV) and electron beam (EB) curable coatings on metal.

PERFORMANCE HIGHLIGHTS

EBECRYL 170 is characterized by:

- Low viscosity
- Acid functionality

UV/EB curable formulated products containing EBECRYL 170 are characterized by:

- Good adhesion to metal substrates
- Improved reactivity (relative to EBECRYL 168)

The actual properties of UV/EB cured products also depend on the selection of other formulation components such as reactive diluents, additives and photoinitiators.

SUGGESTED APPLICATIONS

Formulated UV/EB curable products containing EBECRYL 170 may be applied via direct or reverse roll, offset gravure, metering rod, slot die, knife over roll, air knife, curtain and immersion coating methods. EBECRYL 170 is recommended for use in:

- General metal coatings and primers
- Coatings for galvanized pipe and tube
- Coil coatings
- Solder resist formulations

SPECIFICATIONS

	VALUE
Acid value, mg KOH/g	270-330
Appearance	Clear to slightly opalescent
Color, Gardner, max.	6
Viscosity, 25°C, cP/mPa·s	2250-3750

TYPICAL PHYSICAL PROPERTIES

Density, g/ml at 25°C	1.33
Functionality, theoretical ⁽¹⁾	~1.5
Oligomer, % by weight	100

NOTES ON USAGE

Typical usage level is between 1% and 5% by weight of the total formulation. Due to its acidic character, EBECRYL 170 can undergo hydrolysis, and therefore formulations containing EBECRYL 170 should be protected from humidity. Since EBECRYL 170 can react with alkaline materials, free amines, amino acrylates, basic pigments and N-vinyl-2-pyrrolidone should not be used in combination with EBECRYL 170.

Formulations may exhibit turbidity with the addition of EBECRYL 170, though such turbidity may not be immediately apparent. The presence of turbidity is not normally indicative of coating performance problems, though in severe instances, separation or precipitation may occur. EBECRYL 170 is completely soluble in OTA-480⁽³⁾, TMPTA⁽³⁾, and TPGDA⁽³⁾, with limited solubility in HDDA⁽³⁾.

PRECAUTIONS

Before using EBECRYL 170, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

Contamination of EBECRYL 170 with acetone or other ketones can cause coloration of the product during storage.

See the SDS for the recommended storage temperature range for EBECRYL 170.

Please refer to the allnex Guide to Safety and Handling of Acrylate Oligomers and Monomers for additional information on the safe handling of acrylates.

(1) Theoretical determination based on the undiluted oligomer.

(2) Product of allnex

www.allnex.com

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.