

EBECRYL® 445

Chlorinated Polyester

July 2017



INTRODUCTION

EBECRYL 445 is a reactive chlorinated polyester resin diluted 40% with the reactive diluent trimethylolpropane triacrylate (TMPTA)⁽¹⁾. EBECRYL 445 is not based on bisphenol A raw materials, and is tin-free. EBECRYL 445 exhibits good lithographic behavior and pigment wetting properties, and fast cure response in ultraviolet light (UV) curable coatings and inks. Cured films of EBECRYL 445 display good adhesion to metals, and paper.

PERFORMANCE HIGHLIGHTS

EBECRYL 445 is characterized by:

- Good wet lithographic behavior
- Fast curing
- Low odor

UV/EB cured formulations based on EBECRYL 445 are characterized by the following performance properties:

- Good adhesion to metals, and paper

The actual properties of UV/EB cured formulations also depend on the selection of the other formulation components, such as reactive diluent(s), additives and photoinitiators.

SUGGESTED APPLICATION

UV/EB curable formulations containing EBECRYL 445 may be applied by lithographic, screen, gravure, direct or reverse roll, and curtain coating methods.

EBECRYL 445 is recommended for use in:

- Wet lithographic inks and coatings for paper, and metals
- Adhesion promoter for inks and coatings on metals, and paper

SPECIFICATIONS

	VALUE
Acid value, mg KOH/g, max	10-25
Appearance	Clear liquid
Color, Gardner scale, max.	3
Viscosity, 60°C, cP/mPa-s	1350-1650

TYPICAL PROPERTIES

Density, g/ml at 25°C	1.28
Resin, % by weight	60
TMPTA, % by weight	40

VISCOSITY REDUCTION

EBECRYL 445 can be further diluted with TMPTA or other reactive monomers such as, 1,6-hexanediol diacrylate (HDDA)⁽¹⁾, tripropylene glycol diacrylate (TPGDA)⁽¹⁾, or propoxylated glycerol triacrylate (OTA-480)⁽¹⁾. Although viscosity reduction can be achieved with non-reactive solvents, reactive diluents are preferred because they are essentially 100 percent converted during UV/EB exposure to form a part of the coating or ink, thus reducing solvent emissions. The specific reactive diluents used will influence performance properties such as hardness and flexibility.

PRECAUTIONS

Before using EBECRYL 445, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

See the SDS for the recommended storage temperature range for EBECRYL 445.

Please refer to the allnex Guide to Safety and Handling of Acrylate Oligomers and Monomers for additional information on the safe handling of acrylates.

(1) Product of allnex

www.allnex.com

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.