

AIRASE® 8070

DESCRIPTION

AIRASE® 8070 is an effective deaerator concentrate based on polyether siloxane technology. Very effective against micro-foam. Offers good compatibility.

KEY BENEFITS

- highly suitable for airless or airmix applications
- recommended for high- to medium-viscosity formulations
- good balance of compatibility and effectiveness

APPLICATION RECOMMENDATION

Brush application/roller application



Airless spraying



Compressed air spraying



Flexo/gravure printing



Dip coating, flow coating, curtain coating



Flooring



SUITABILITY

waterborne	solventborne
●	●
2-pack 100%	radiation-curing
●	●
addition to the grinding stage	addition to the let-down stage
●	●

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- General industrial coatings
- Wood coatings
- Pigment concentrates
- Architectural paints

TECHNICAL DATA

active matter content	100 %
appearance	clear colored liquid
chemical description	polyether siloxane copolymer
solvent	-

SOLUBILITY

Water	Ethanol
●	●
TPGDA	Acetone
●	●
Butylacetate	Mineral Spirits
●	●

● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.1 - 1.0 %

PROCESSING INSTRUCTIONS

Can be introduced in the grind and let-down stage.

HANDLING & STORAGE

Keep containers tightly closed in a dry, cool, and well-ventilated place. Mix thoroughly before use. Product is freeze-thaw stable but may separate on standing or freezing; bring product to 20-30°C and mix thoroughly before use.

MSDS & REGULATORY INFORMATION



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Resource Efficiency GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com