

D.E.R.™ 692H

Please use this Technical Data Sheet (TDS) in conjunction with this product's country-specific Safety Data Sheet (SDS) and the Safe Use conditions as described therein. Current Safety Data Sheets can be requested from Olin at info@olinbc.com

Description Low molecular weight "2.5-type" epoxy resin with Flow modifier.

Applications • Industrial Coatings: Powder

Properties	Nominal Value	(English)	Nominal Value	(SI)
EEW	660 to 720	g/eq	660 to 720	g/eq
Viscosity, absolute (302°F (150°C))	1600 to 2400	mPa·s	1600 to 2400	mPa·s
Softening Point	192 to 207	°F	89 to 97	°C

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ Typical properties: these are not to be construed as specifications.

Product Stewardship	Olin Corporation has a fundamental concern for all who make, distribute, and use its products, and environment in which we live. This concern is the basis of our Product Stewardship philosophy by we assess the health and environmental information on our products and then take the appropriat to protect employee and public health and the environment.						
	Olin encourages its customers and potential users of Olin products to review their applications for such products from the standpoint of human health and environmental quality. To help ensure that Olin produ are not used in ways for which they were not intended or tested, Olin personnel are available to assist customers in dealing with ecological and product safety considerations. Your Olin sales representative or arrange for the proper contacts.						
Regulatory Datasheets (RDS)	Olin Corporation provides information on the regulatory status of its products under prominent regulatory programs in the Regulatory Datasheet (RDS). Regulatory Datasheets can be requested from Olin at info@olinbc.com						
Disclaimer	Notice: No freedom from any patent or other intellectual property rights owned by Olin or others is to be inferred. Olin assumes no obligation or liability for the information in this document. The information provided herein is presented in good faith and is based on the best of Olin's knowledge, information, and belief. Since use conditions at non-Olin facilities are beyond Olin's control and government requirements may differ from one location to another and may change with time, it is solely the Buyer's responsibility to determine whether Olin's products are appropriate for the Buyer's use, and to assure the Buyer's workplace, use, and disposal practices are in compliance with applicable government requirements. Consequently, Olin assumes no obligation or liability for use of these materials and makes no warranty, express or implied. The user of the information provided is solely responsible for compliance with any applicable government requirements. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.						
Contact Information	USA: China: Germany: Italy: Latin America: Singapore: United Kingdom:	1-844-238-3445 86-4008859485 49-41417693000 39-0694805761 55-1151884105 65-31632006 44-8000869047	Canada: France: Hong Kong: Japan: Russia: South Korea:	1-877-304-4442 33-176361145 852-58081886 81-345406770 7-4996092327 82-260221296			
www.OlinEpoxy.com							

⊘lin™