

# EBECRYL® 151

Grinding Vehicle for UV Inkjet

May 2017



## INTRODUCTION

EBECRYL 151 is a pigment grinding vehicle for energy curable inkjet inks. When used in conjunction with EBECRYL 152 (a letdown vehicle), jettable, stable inks are obtained for use in drop-on-demand piezo inkjet systems.

## PERFORMANCE HIGHLIGHTS

- Produces low viscosity pigment dispersions and inks; inks are about 30 cP at 25°C
- Suitable for grinding pigments in a bead mill
- Low odor
- High reactivity
- Good adhesion to treated plastics and coated papers
- Cured ink has high gloss, and good scratch and solvent resistance
- Results in inks with easy priming, no face plate wetting, no nozzle loss with continuous printing, good stability and jettable, no satellite formation, and no dot gain

## SUGGESTED APPLICATIONS

EBECRYL 151 is recommended as a pigment grinding vehicle for drop-on-demand piezo inkjet head systems. Inks based on EBECRYL 151 are well suited to the following markets: banner and outdoor, POP, labels and packaging, fleet markings, decorative printing and other large format inkjet applications.

## STARTING POINT FORMULATION

COMPONENT	PBW
Pigment	15-25
EBECRYL 151	75-85
Stabilizer	0.5-0.1
Additives	0.2-0.5

Please refer to the Technical Bulletin for EBECRYL 151 and EBECRYL 152 for more detailed information.

## SPECIFICATIONS

	VALUE
Appearance	Clear liquid
Color, Gardner scale, max.	5
Viscosity, 25°C, cP/mPa·s	50-150

## TYPICAL PHYSICAL PROPERTIES

Density, g/ml at 21.5°C	1.09
Solids, %	100
Surface tension, Du Noüy, mN/m <sup>(1)</sup>	38.6

## PRECAUTIONS

Before using EBECRYL 151, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

## STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

See the SDS for the recommended storage temperature range for EBECRYL 151.

Please refer to the allnex Guide to Safety and Handling of Acrylate Oligomers and Monomers for additional information on the safe handling of acrylates.

(1) mN/m = dynes/cm

[www.allnex.com](http://www.allnex.com)

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or \* as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.