

CYMEL[®] NF 3030 resin

PRODUCT DESCRIPTION

CYMEL NF 3030 resin is a formaldehyde-free crosslinking agent supplied in water. It was designed primarily for use in 2 pack, ambient or forced cure, water-borne conversion varnishes for industrial wood when formulated with Viacryl SC 6834w/42WA amine-free acrylic emulsion. Resulting formulas exhibit superior catalyzed pot life relative to isocyanate-based conversion varnishes. The resulting coatings have excellent appearance, early hardness, resistance properties, and hot/cold cycle flexibility.

BENEFITS

- Does not contain formaldehyde
- Does not emit formaldehyde during curing process
- Excellent compatibility with a variety of OH functional resins
- Fast cure response in ambient and heat cure applications
- Extended catalyzed coating stability or pot life in 2K systems.

APPLICATION AREAS

- Industrial wood coatings

PHYSICAL PROPERTIES

Property	Range	Method
Appearance	Clear Liquid	Visual
Non-volatile by wt.	40-45%	Pan, 1 hr/125°C
Viscosity, 23°C	< 300 mPa·s	Dynamic
Color, APHA	≤ 200	ISO 6271

SOLUBILITY

Alcohols	Partially Soluble
Esters	Insoluble
Ketones	Insoluble
Aromatic hydrocarbons	Insoluble
Water	Soluble

COMPATIBILITY

Acrylic resins	Excellent
Alkyd resins	Excellent
Polyester resins	Excellent

BACKBONE POLYMER SELECTION

CYMEL NF 3030 resin is an effective crosslinking agent for alkyd, polyester and acrylic polymers containing primary hydroxyl functionality. Reactivity with secondary hydroxyl sites is limited under ambient cure. CYMEL NF 3030 resin has a high Tg and should be paired with softer polyols (Tg < 30°C) to avoid film checking or cracking. The equivalent weight of CYMEL NF 3030 is ~85 g/eq (solids basis). Binder ratios can vary from 85/15 to 70/30 depending upon the equivalent weight of the polyol.

CATALYSIS

For ambient or low bake applications, it is recommended to use 1.0% CYCAT[®] 4040 catalyst based on weight of total binder solids. For high bake applications, the addition of catalyst isn't required as long as the acid number of the primary film former is >5.

STORAGE STABILITY

CYMEL NF 3030 resin has a shelf life of 180 days from the date of manufacture when stored at temperatures between 5°C and 30°C. Avoid freezing.

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.

February 2016