

SUKOREZ SU-625

Hydrogenated hydrocarbon resin

1st/9/2012

SUKOREZ SU-625 is a fully hydrogenated waterwhite hydrocarbon resin. SUKOREZ SU-625 is characterized by water white color, good thermal stability and high temperature resistance. It is specialized in film modification and primarily used to enhance the performance. Also it is used in SIS based hot melt PSAs and hot melt adhesives with good compatibility with EVA, polyolefins and etc.

SPECIFICATIONS

Softening Point (Ring & Ball, °C)	120-130	ASTM E 28
Color (50% Toluene Solution, HAZEN)	Max.30	ASTM D 1209

TYPICAL PROPERTIES

Specific Gravity (20/20°C)	1.08	ASTM D 71
Softening Point (Ring & Ball, °C)	125	ASTM E 28
Color (50% Toluene Solution, HAZEN)	15	ASTM D 1209
Viscosity	BRF, @160°C, cps	8,500
	BRF, @180°C, cps	1,300
Molecular Weight (GPC, Mw)	600	G.P.C

Kolon Company and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

PACKAGING

SUKOREZ SU-625 is available both in big bags of 500kgs net weight and in multi-ply paper bags of 25kgs net weight.

STORAGE

Pelletized forms of resins may be blocked or lumped in hot weather climates or if stored near heat sources. Inside storage is recommended and keep at temperature not exceeding 30°C

REGULATORY STATUS

SUKOREZ SU-625 is in compliance with the requirements of the U.S FDA for following sections.

175.105	Adhesives
175.125	Pressure sensitive adhesives
175.300	Resinous and polymeric coatings
175.320	Resinous and polymeric coatings for poly olefin films
176.170	Components of paper and paperboard in contact with aqueous and fatty foods.
176.180	Components of paper and paperboard in contact with dry food
177.1210	Closures with sealing gaskets for food containers
177.1520	Olefin polymers
177.2600	Rubber articles intended for repeated use

KOLON INDUSTRIES, INC.

HEAD OFFICE : 10TH FL., KOLON TOWER 1-23, BYULYANG-DONG GWACHEON-CITY KYUNGGI-DO, KOREA
TEL) 82-2-3677-6105 FAX) 82-2-3677-6191

YEOSU PLANT : SANDANJUNGANG-RO 213, YEOSU, JEONNAM, KOREA
TEL) 82-61-690-9860 FAX) 82-61-690-9899
