

# SURFYNOL® DF-58

## DESCRIPTION

SURFYNOL® DF 58 is an effective defoamer concentrate based on polyether siloxane technology. Excellent foam knockdown.

## KEY BENEFITS

- highly suitable for fast foam knock-down
- in low addition levels, also suitable for low-viscosity formulations
- suitable in combination with defoamers or deaerators that suppress foam build

## APPLICATION RECOMMENDATION

### Brush application/roller application



### Airless spraying



### Compressed air spraying



### Flexo/gravure printing



### Dip coating, flow coating, curtain coating



### Flooring



## SUITABILITY

waterborne	solventborne
●	●
2-pack 100%	radiation-curing
●	●
addition to the grinding stage	addition to the let-down stage
●	●

● not suitable ● partly suitable ● suitable

## TYPICAL APPLICATIONS

- Wood coatings
- Architectural paints
- Pigment concentrates
- Printing Inks

## TECHNICAL DATA

<b>active matter content</b>	100 %
<b>appearance</b>	turbid, colorless to colored liquid
<b>chemical description</b>	polyether siloxane copolymer, contains hydrophobic particles
<b>solvent</b>	-

## SOLUBILITY

Water	Ethanol
●	●
TPGDA	Acetone
●	●
Butylacetate	Mineral Spirits
●	●

● not soluble ● partly soluble ● soluble

## RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.05 - 0.5 %

## PROCESSING INSTRUCTIONS

Can be introduced in the grind and let-down stage.

## HANDLING & STORAGE

Keep containers tightly closed in a dry, cool, and well-ventilated place. To avoid ignition of vapors by static electricity discharge, all metal parts of the equipment must be grounded. Keep away from heat and sources of ignition. Keep away from oxidizers. Protect from freezing. Mix thoroughly before use.

## MSDS & REGULATORY INFORMATION



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Resource Efficiency GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | [www.coating-additives.com](http://www.coating-additives.com)