



# Baerostab X AB/5A

## PRODUCT INFORMATION

|                                |   |             |                               |                  |     |                   |                 |                   |               |
|--------------------------------|---|-------------|-------------------------------|------------------|-----|-------------------|-----------------|-------------------|---------------|
| <b>Description</b>             | Butyl Tin Mercaptide  |             |                               |                  |     |                   |                 |                   |               |
| <b>Typical Properties</b>      | <table><tr><td>Appearance:</td><td>Colorless to yellowish liquid</td></tr><tr><td>Color (Gardner):</td><td>&lt; 2</td></tr><tr><td>Refractive Index:</td><td>1.5030 - 1.5090</td></tr><tr><td>Specific gravity:</td><td>1.104 - 1.134</td></tr></table>   | Appearance: | Colorless to yellowish liquid | Color (Gardner): | < 2 | Refractive Index: | 1.5030 - 1.5090 | Specific gravity: | 1.104 - 1.134 |
| Appearance:                    | Colorless to yellowish liquid   |             |                               |                  |     |                   |                 |                   |               |
| Color (Gardner):               | < 2   |             |                               |                  |     |                   |                 |                   |               |
| Refractive Index:              | 1.5030 - 1.5090   |             |                               |                  |     |                   |                 |                   |               |
| Specific gravity:              | 1.104 - 1.134   |             |                               |                  |     |                   |                 |                   |               |
| <b>Application</b>             | <p>Baerostab X AB/5A is a liquid butyl tin mercaptide stabilizer which is recommended for rigid PVC applications. It has excellent early color performance. Typical applications are window profile, siding, fascia, eavestrough and soffit. Filler loadings should be less than 50 phr.</p> <p>Recommended dosage: 0.7 to 2.5 phr, depending on application.</p> |             |                               |                  |     |                   |                 |                   |               |
| <b>Food Packaging Approval</b> | Baerostab X AB/5A may not be used in manufacturing of food packaging material. It is not FDA sanctioned.  |             |                               |                  |     |                   |                 |                   |               |
| <b>Handling</b>                | A material safety data sheet for the handling of this product is available on request.  |             |                               |                  |     |                   |                 |                   |               |
| <b>Storage</b>                 | Dry storage at room temperature is recommended.<br>Once opened, packaging should be firmly closed.  |             |                               |                  |     |                   |                 |                   |               |

The data herein is deemed accurate by the supplier, however, is provided for informational purposes only and creates no warranties, express or implied. As the consumer controls application of the product, this information does not constitute a warranty of merchantability, fitness for a particular use or recommendations to practice any patented invention without a license.