



## Product Information

---

### Baeropol T-Blend 1214 TX

**Description** A synergistic antioxidant blend for polymer stabilization. High bulk density, free flowing pastille.

Properties	Test	Specification	Typical Property
	Ash	15.5-20%	17.7%
	Phenolic AO Content (%)	26 - 31%	28.6%
	Phosphite AO Content (%)	12 – 17%	14.3%

**Features** Baeropol T-Blend 1214 TX is a blend of phenolic antioxidant (tetrakis[methylene-3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate]methane), a phosphite (tris(2,4-di-tert-butylphenyl)phosphite), and a high quality vegetable fatty acid derived stabilizer. The efficacy for Baeropol T-Blend 1214 TX allows it to be a direct drop-in for most traditional binary antioxidant blends.

**Performance** The synergistic stabilizer blend allows for the partial replacement of phosphites in traditional B-Blends while improving overall performance.

Baeropol T-Blend 1214 TX provides excellent melt stability in standard polyethylene and polypropylene resins during normal processing conditions. It improves color for single or multiple extrusions. In many applications Baeropol T-Blend 1214 TX enhances the overall performance of resin.

The granule form of the product minimizes dust exposure and minimizes housekeeping issues in the work environment. The free-flowing nature of granules avoids problems with bridging and caking and facilitates use in most bulk handling or conveying and automated weighing and metering systems.

**Quality Control** A modern, state-of-the-art plant process with strict control ensures consistent quality in chemical and mechanical properties.

**Regulatory** Meets FDA requirements under 21 CFR 178.2010 and Regulation Directive (EU) 10/2011 for additives used in plastic materials and articles intended to come into contact with foods.

Further detailed regulatory information is available upon request.

**Packaging** Standard semi-bulk packaging in supersacks and 40 x 50 lb. multiwall bags on stretch wrapped pallet is available.

**Storage** Storage in dry areas at normal ambient temperatures is recommended. Open containers of unused product should be firmly closed for storage.

TDS-Baeropol T-Blend 1214 TX 180326

**NOTICE:** Although the information and recommendations contained in this document (hereinafter "Information") are presented in good faith and believed to be correct at the date of their publication, BAERLOCHER makes no representations or warranties as to the completeness or accuracy of Information.

Information is supplied upon the condition that the persons or entities receiving same will make their own determination as to its suitability for their purposes prior to their use. In no event, will BAERLOCHER be responsible or liable for any loss of profits, lost goodwill, direct, special, indirect, incidental, or consequential damages of any nature whatsoever, including without limitation lost revenue, resulting from the use of or reliance upon Information or the product to which Information refers.

Nothing contained in this disclaimer is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent or intellectual property right, and BAERLOCHER makes no representation or warranty, express or implied, that the use thereof will not infringe any patent or intellectual property rights.

No representations or warranties, either expressed or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which Information refers.