

## VERSAL YELLOW 4GP



### Characteristic

C. I.	Pigment Yellow 155
C. I. No.	200310
CAS No.	68516-73-4
Chemical Class	Bisacetoacetarylide

### Properties

Oil Absorption [ml/100 g]	64
Density [g/cm <sup>3</sup> ]	1,4
Bulking Volume [l/kg]	5,2

### Fastness

Linseed Oil	4-5
White Spirite	5
DEHT	5
Xylene	4-5
Acetone	3-4
Butylacetate	4
Ethanol	4-5
Water	5
HCl 2.5%	5
NaOH 2.5%	5
Light - Full Shade	P 7-8
Light - 1/1	7-8
Light - 1/3	7
Weather - Full Shade	P 5
Weather - 1/1	4-5
Weather - 1/3	4
Overspray	5
Heat Resistance [°C]	P 260
Migration	4-5

P - in Plastics

### Application Possibilities

- Plastics - Polyolefines ●
- Plastics - PVCp ●



Synthesia, a.s., Semtín 103, 530 02 Pardubice, Czech Republic  
 Identification number: 60108916 • VAT: CZ60108916

phone: +420 466 821 111 • fax: +420 466 822 900 • e-mail: [synthesia@synthesia.eu](mailto:synthesia@synthesia.eu)  
[www.synthesia.eu](http://www.synthesia.eu)



Plastics - PP Fibers

● main application



○ side application

**Other Informations**

Shelf Life

48 months

**Testing methods**
**Density**

 - determined by ČSN EN ISO 787-10: 1997 (67 0520) in  $\text{g/cm}^3$ 
**Bulking Volume**

- denotes the volume of 1 kg of loosely poured pigment, expressed in litres

**Oil Absorbtion**

- determined by ČSN EN ISO 787-5: 1997 (67 0520) in ml/100 g pigment

**Fastness to Solvents**

- colouring of solvent after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one

**Fastness to Reagents**

- colouring of reagents after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one

**Light Fastness - Xenotest**

- determined by ČSN EN ISO 105-B02: 2000 (80 0147) and evaluated in 1/3 and 1/1 of standard depth and in full shade; determined according to blue scale, by it degree 1 denotes the lowest fastness, degree 8 the highest one

**Weathering Fastness - Xenotest**

- determined by ČSN EN ISO 105-B04: 1998 (80 0171) and evaluated in 1/3 and 1/1 of standard depth and in full shade; determined according to grey scale, by it degree 1 denotes the lowest fastness, degree 5 the highest one

**Overspray Fastness**

- assessment of bleeding into a white nitrocellulose combination lacquer for 60 min. at 70 °C against ISO grey scale; by it degree 1 denotes the lowest fastness, degree 5 the highest one

**Heat Resistance**

- the values quoted indicate up to what temperature the pigments do not significantly alter; these are guide values which can be influenced by the binder used and the period of exposure to high temperature

**Migration Fastness**

- assessment of bleeding into a white polyvinylchloride sheet for 24 h at 70 °C against ISO grey scale; by it degree 1 denotes the lowest fastness, degree 5 the highest one; no data means that the pigment is not recommended for dyeing of PVC

**Fastness to plasticizers**

- colouring of plasticizer (diethylhexylterephthalate) after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one