

# D.E.H.™ 20

Please use this Technical Data Sheet (TDS) in conjunction with this product's country-specific Safety Data Sheet (SDS) and the Safe Use conditions as described therein. Current Safety Data Sheets can be requested from Olin at info@olinbc.com

### Description

D.E.H. 20 Epoxy Curing Agent is an economical, liquid diethylenetriamine (DETA) aliphatic polyamine hardener that provides a short pot-life and cures in minutes with standard unmodified liquid epoxy resins.

D.E.H. 20 Epoxy Curing Agent is used for civil engineering applications, maintenance paints, and in the manufacture of epoxy-amine adducts. It is also used in adhesives, epoxy composite applications and as an accelerator for polyamide curing agents. In electrical applications, D.E.H. 20 Epoxy Curing Agent is used for casting, potting and encapsulation.

NOTE: This amine curing agent is hygroscopic and may pick up moisture and carbon dioxide from the atmosphere.

### **Applications**

- Adhesives
- Building & Civil Engineering
- · Castings / Potting / Encapsulation / Tooling
- · Composites
- · Industrial Coatings: Marine and Protective

Properties	Nominal Value	(English)	Nominal Value	(SI)
AHEW (Appr.)	21	g/eq	21	g/eq
Viscosity, absolute (77°F (25°C))	4.00 to 8.00	mPa·s	4.00 to 8.00	mPa·s
Colour (Max. Pt-Co.)	30		30	
Density (77°F (25°C))	0.95	g/cm³	0.95	g/cm³

#### **Notes**

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.

## Product Stewardship

Olin Corporation has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis of our Product Stewardship philosophy by which we assess the health and environmental information on our products and then take the appropriate steps to protect employee and public health and the environment.

Olin encourages its customers and potential users of Olin products to review their applications for such products from the standpoint of human health and environmental quality. To help ensure that Olin products are not used in ways for which they were not intended or tested, Olin personnel are available to assist customers in dealing with ecological and product safety considerations. Your Olin sales representative can arrange for the proper contacts.

# Regulatory Datasheets (RDS)

Olin Corporation provides information on the regulatory status of its products under prominent regulatory programs in the Regulatory Datasheet (RDS). Regulatory Datasheets can be requested from Olin at info@olinbc.com

#### **Disclaimer**

Notice: No freedom from any patent or other intellectual property rights owned by Olin or others is to be inferred. Olin assumes no obligation or liability for the information in this document. The information provided herein is presented in good faith and is based on the best of Olin's knowledge, information, and belief. Since use conditions at non-Olin facilities are beyond Olin's control and government requirements may differ from one location to another and may change with time, it is solely the Buyer's responsibility to determine whether Olin's products are appropriate for the Buyer's use, and to assure the Buyer's workplace, use, and disposal practices are in compliance with applicable government requirements. Consequently, Olin assumes no obligation or liability for use of these materials and makes no warranty, express or implied. The user of the information provided is solely responsible for compliance with any applicable government requirements. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

# Contact Information

USA: 1-844-238-3445 1-877-304-4442 Canada: China: 86-4008859485 France: 33-176361145 Germany: 49-41417693000 Hong Kong: 852-58081886 81-345406770 39-0694805761 Italy: Japan: Latin America: 55-1151884105 Russia: 7-4996092327 Singapore: 65-31632006 South Korea: 82-260221296 United Kingdom: 44-8000869047

www.OlinEpoxy.com

