



CARPENTER

CARPOL[®] NIONIC[™] 850 Polyglycol

CARPOL[®] NIONIC[™] 850 Polyglycol is a nonionic surfactant with a chemical structure designed to make it act as a defoamer in many applications. Even at very low concentrations, CARPOL[®] Nionic[™] 850 can be used to reduce the superficial tension of liquids, including high viscosity liquids. Defoaming performance is a function of cloud point and end use temperature. These materials are water soluble at low temperatures and will flocculate when warmed above their cloud point.

Typical Physical Properties

Actives (wt%)	100
Cloud Point (°C)	19
HLB ¹	<2
Contains EO	Yes
Pour Point (°C)	-14
Appearance	Clear Liquid
Viscosity at 25 °C (cP)	850
Density at 25 °C (g/ml)	1.03
CMC	—
Surface Tension (dynes/cm)	33.6
Ross-Miles Foam Height ² , mm	(35/18/15/15)
Draves 20 sec Wetting Conc ³ (wt%)	0.08

The values above are not specifications

Benefits

- Foam Control
- Surface Tension Reduction
- Viscosity Modifier
- Thermal Stability
- Wetting Agent

Applications

- Food Processing
- Fermentation
- Dispersant
- Emulsion Breaker
- Cleaning Aid
- Oil & Gas
- Agriculture

¹HLB Values were measured using UPLC w/ Evaporative Light Scattering Detection against known standards

²ASTM D1173-07: mm at 0.1 wt% actives, 25°C, t = 0 / t = 1 min / t = 3 min / t = 5 min

³ASTM D2281-10, Evaluation of Wetting Agents by the Skein Test

CARPOL[®] NIONIC[™]



Storage Information

CARPOL® NIONIC™ 850 Polyglycol will absorb water if the product container is not secured properly. This may affect reactivity, appearance, and performance. Therefore, it is advised that all receptacles containing this material be tightly fastened and stored in a dry place.

Consult the Safety Data Sheet for additional information.

Health and Safety Information

Health and safety information is available in the form of a Safety Data Sheet. This literature, describing proper precautions and personal protective gear, is available for review. To receive this information please contact a Carpenter Co. representative.

Ordering and Shipping Options

Sample Sizes

1 quart

1 gallon

5 gallon

Products Packaged/Shipped

Drum 460 lb net wt.

Totobin 2,300 lb net wt.

Tankwagon 40,000-45,000 lb net wt.

Railcar 185,000-189,000 lb net wt.

For additional information please contact:

Carpenter Co.

Chemicals Division

Customer Service 800-260-5373

5016 Monument Avenue

Richmond VA 23230

www.carpenter.com



Updated July 2016

Important: The information contained in this product data sheet is offered for your consideration, investigation, and verification. The data is presented in good faith and is believed to be reliable. Carpenter, however, makes no representation as to the completeness or accuracy. Carpenter makes no warranty, express or implied, with respect to the data contained herein. Carpenter cannot anticipate all conditions under which this data and the product may be used. The conditions of handling, storage, use, and disposal of the product are beyond Carpenter's control. Thus we expressly disclaim responsibility or liability for any loss, damage, or expense arising out of reliance on the information contained herein. You are advised to make your own determination as to safety, suitability, and appropriate manner of handling, storage, use, and disposal. For further information please consult the appropriate Carpenter Safety Data Sheet.

Warning: These products can be used to prepare a variety of polyurethane products. Polyurethanes are organic materials and must be considered combustible.

