

EBECRYL® LEO 10551

Amine Modified Polyether Acrylate

Produced following Good Manufacturing Practices (GMP)

March 2018



INTRODUCTION

EBECRYL LEO 10551 is a low viscosity amine modified polyether acrylate oligomer that provides low extractables, low odor and low migration after UV or EB curing.

EBECRYL LEO 10551 is recommended for use in low odor and low migrating UV overprint varnishes (OPV's) and inks for indirect food packaging applications.

PERFORMANCE HIGHLIGHTS

EBECRYL LEO 10551 is characterized by:

- Low viscosity

UV/EB cured products based on EBECRYL LEO 10551 are characterized by the following performance properties:

- Good cure response
- Good flexibility
- High gloss
- Low extractables
- Low odor
- Low migration

The actual properties of UV/EB cured products also depend on the selection of other formulation components such as reactive diluents, additives and photoinitiators.

SUGGESTED APPLICATIONS

EBECRYL LEO 10551 is recommended as the main oligomer for low extractable, low odor overprint varnishes and as the letdown for flexographic inks for indirect food packaging and related applications. It is also suitable for screen and gravure application.

MUTAGENICITY ASSESSMENT

The following mutagenicity study has been conducted on EBECRYL LEO 10551 in compliance with Good Laboratory Practice standards and according to the specific OECD Guidelines for Testing of Chemicals as follows:

- Ames test – OECD 471

No significant increases in the frequency of revertant colonies were found for any of the bacterial strains, either with or without metabolic activation. This material was found to be nonmutagenic under the conditions of this study. The mutagenicity behavior of an acrylate with a structure similar to that of EBECRYL LEO 10551 has also been examined and, after extensive testing, was found to be nonmutagenic. The weight of evidence of all findings on the "acrylates" category indicates that the acrylates are not mutagenic. We use these category effects to substitute for testing on acrylates. This is consistent with contemporary strategies (compliant with REACH) to minimize the toxicological testing of animals and utilize alternative methods to establish the safety of industrial chemicals (more information available upon request).

www.allnex.com

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.

SPECIFICATIONS

	VALUE
Appearance	Clear liquid
Color, Gardner scale, max.	2
Viscosity, 25°C, cP/mPa-s	60-90

TYPICAL PROPERTIES

	VALUE
Density, g/ml at 25°C	1.09
Functionality, theoretical	2.5
Molecular weight, g/mol	500
Residual acrylic acid, ppm	<200
Residual amine, ppm	<200
Residual solvent, ppm	<100
Weight/amine, theoretical	1079

PRECAUTIONS

Before using EBECRYL LEO 10551, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

See the SDS for the recommended storage temperature range for EBECRYL LEO 10551.

Please refer to the allnex Guide to Safety and Handling of Acrylate Oligomers and Monomers for additional information on the safe handling of acrylates.