



Baerolub® PA-7015

Description Paraffin and oxidized PE wax blend

Properties	<u>Test</u>	<u>Specification</u>	<u>Typical Property</u>
	Congealing point (F)	160-170	164
	Brookfield Viscosity (CPS)	12-18	15
	Needle Penetration @77F mm/10	5-12 mm/10	8
	Color	Report	Pass

Performance Baerolub PA 7015 is a paraffin wax and low density oxidized PE wax blend. It is the primary external lubricant for PVC pipe manufacturing to control proper fusion, metal release of the polymer melt, and melt flow. As a primary external lubricant its function is to delay fusion of PVC in the extruder, which is balanced by the internal lubricant(s) such as calcium stearate to balance fusion times and processability.

Quality Control A modern, state-of-the-art plant process with strict control ensures consistent quality in chemical and mechanical properties.

Regulatory This product is in compliance with Federal Regulations 21-CFR 178.3710 and 172.886. Baerolub PA 7015 is currently pending approval for NSF Standard 14 listed ingredient for use in potable pipe.

Packaging Standard 40 x 50 lb. multiwall bags on stretch wrapped pallet. Bulk packaging in supersacks is available.

Storage Storage in dry areas at normal ambient temperatures is recommended. Open containers of unused product should be firmly closed for storage.

TDS-5868 180321

NOTICE: Although the information and recommendations contained in this document (hereinafter "Information") are presented in good faith and believed to be correct at the date of their publication, BAERLOCHER makes no representations or warranties as to the completeness or accuracy of Information.

Information is supplied upon the condition that the persons or entities receiving same will make their own determination as to its suitability for their purposes prior to their use. In no event, will BAERLOCHER be responsible or liable for any loss of profits, lost goodwill, direct, special, indirect, incidental, or consequential damages of any nature whatsoever, including without limitation lost revenue, resulting from the use of or reliance upon Information or the product to which Information refers.

Nothing contained in this disclaimer is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent or intellectual property right, and BAERLOCHER makes no representation or warranty, express or implied, that the use thereof will not infringe any patent or intellectual property rights.

No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which Information refers.