

Issued Date :
 Dec 3, 2019

Effective Date :
 May 2, 2023

Properties/Test Method	Specification	Unit
PK30010 - Surface Area (BET)	Min 11--Max 19.5	m2/g
PKQ0003 - Scott Volume	Min 6--Max 8.3	g/in3
Free Crystalline Si (Supplier COA)	Max 0	*
PKQ0006 - Silicon Carbide Wt. %	Min 98	%
Particle Size Distribution		
PK30012 - Particle Size (D50)	Min .55--Max .68	um

This Specification Sheet is provided for informational purposes. Superior Graphite makes no express or implied representation or warranty regarding the accuracy of the information set forth in this Specification Sheet or regarding any Superior Graphite product or the use thereof (including without limitation, any warranty of quality, merchantability, or fitness for a particular use or purpose), except to the extent otherwise expressly provided in Superior Graphite's Terms and Conditions of Sale. Each customer of Superior Graphite assumes all risk and liability relating to its use of Superior Graphite's products and is responsible for independently testing Superior Graphite's products prior to such customer's use thereof to determine whether such products are fit and suitable for such customer's intended use or purpose. This Specification Sheet is subject to change upon written notice.

Superior Graphite

550 W. Van Buren St., Suite 300
 Chicago, Illinois 60607 USA
 P +1 312 559 2999 | +1 800 325 0337
 F +1 312 559 9064
 CustomerServiceUSA@SuperiorGraphite.com

Superior Graphite Europe Ltd.

Box 1300, SE-85013
 Sundsvall, Sweden
 P +46 60 13 4118
 F +46 60 13 4128
 CustomerServiceEU@SuperiorGraphite.com

**Superior Graphite Import & Export
 (Shanghai) Co. Ltd.**

Room 821, No. 4229 Bao'an Road
 Jiading District, Shanghai 201814, P.R. China
 P +86 21 595 800 75, Ext. 103
 F +86 21 595 800 76
 CustomerServiceChina@SuperiorGraphite.com

