## **Technical Data Sheet**



## Product Identification

Castung® 403 Z-3 is a bodied dehydrated castor oil (DCO) that can be used with pure and modified phenolic resins to impart alkali resistance for can linings, corrosion resistant coatings, traffic paints, ink vehicles and marine finishes. The high viscosity Castung® 403 Z-3 will yield faster processing and drying times than Castung 103 G-H. Castung® 403 Z-3 is excellent for formulating alkyd and copolymer resins, where dehydrated castor oil is well known for its non-yellowing and outstanding color retention characteristics.

	<u>Property</u>	<u>Value</u>
Physical	Composition	100% Dehydrated Castor Oil
<b>Properties</b>	Form	Clear amber liquid
	Acid Value	3
	Color, Gardner	3
	Density, lbs./gal, 25°C	7.90
	Fire Point, COC, °F	640
	Flash Point, COC, °F	580
	Gel Time @ 600°F, minutes	35
	lodine Value	123
	Pour Point, °F	-5
	Refractive Index	1.4863
	Saponification Value	190
	Specific Gravity, 25°C/25°C	0.949
	Viscosity, Gardner	Z-2
Applications	Produces high quality durable vehicles	
	Light colored, non-yellowing films	
	Upgrade primary binder systems	
	Excellent pigment wetting and color development	
	Imparts excellent flow and levelling properties	

For toxicity or regulatory information please consult the Material Safety Data Sheet.

Information contained in this technical data sheet is believed to be accurate. Vertellus Performance Materials Inc. assumes no liability and makes no warranty or representation that the information is correct or complete and EXPRESSLY DISCLAIMS ALL REPRESENTATIONS OR WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Final determination of suitability of any material and issues of patent infringement is the sole responsibility of the user who alone knows the conditions of intended use. Our customers should ensure that any product incorporating a Vertellus ingredient is safe for its intended use pursuant to applicable law and that any necessary disclosures to consumers have been made.

Vertellus Performance Materials Inc., 2110 High Point Road, Greensboro, NC 27403 USA

USA Tel: 800-227-2436 USA Fax: 336-854-4058 USA Email: VPM-TechServices@vertellus.com

Web: www.vertellus.com