HIKOTACK P-90S

Rev.12 1st/Jan/2015

Aromatic hydrocarbon resin

HIKOTACK P-90S is pale yellow thermoplastic resin obtained from polymerizing unsaturated aromatic olefins and diolefins derived from the process of thermal cracking of naphtha. The major usages are rubber compounding agent for tires, tubes, rubber coated clothes. And this grade also can be used as tackifier for Ethylene Vinyl Acetate(EVA) based hot melt adhesive(HMA), water repellent agent, concrete curing agent and binder for asphalt.

SPECIFICATIONS

Softening Point (Ring & Ball, °C)	90-100	ASTM E 28
Color (50wt% Solution in Toluene, Ga.#)	Max.8	ASTM D 1544
Acid Value (KOH mg/g)	Max.0.1	ASTM D 974
Bromine Number (Br.cg/g)	Max.30	ASTM D 1159
TYPICAL PROPERTIES		
Specific Gravity (20/20°C)	1.08	ASTM D 71
Softening Point (Ring & Ball, °C)	98	ASTM E 28
Color (50wt% Solution in Toluene, Ga.#)	5.5	ASTM D 1544
Color Stability (@200°C, 3hrs, Ga.#)	9	Molten Resin
Acid Value (KOH mg/g)	0.04	ASTM D 974
Bromine Number (Br.cg/g)	20	ASTM D 1159
Melt Viscosity BRF, @160°C, cps	350	ASTM D 3236
@180°C, cps	125	
Molecular Weight (GPC, Mw)	1,200	G.P.C

Kolon Industries and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determation of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

PACKAGING

HIKOTACK P-90S is available both in big bags of 500kgs net weight and in multi-ply paper bags of 25kgs net weight.

STORAGE

Pelletized forms of resins may block or lump in hot weather climates or if stored near heat sources. Inside storage is recommended and keep at temperature not exceeding 30°C

REGULATORY STATUS

HIKOTACK P-90S is in compliance with the requirements of the U.S FDA for following sections.

175.105 Adhesives
175.300 Resinous and polymeric coatings
177.1210 Closures with sealing gaskets for food containers
177.2600 Rubber articles intended for repeated use

WKOLON INDUSTRIES

HEAD OFFICE: 15TH FL, KOLON TOWER, KOLON-RO 11, GWACHEON-CITY, GYEONGGO-DO, KOREA (427-709)

TEL) 82-2-3677-6124 FAX) 82-2-6280-6192

ULSAN PLANT: NAM-GU, SAPYEONG-RO 33, ULSAN-CITY, KOREA (680-180)

TEL) 82-52-259-8130 FAX) 82-52-259-8149