TEGO® Foamex 811

DESCRIPTION

TEGO* Foamex 811 is an effective defoamer concentrate based on polyether siloxane technology. Broad usability with an excellent balance of effectiveness and compatibility.

KEY BENEFITS

- recommended for addition to the grinding and let-down stage
- good balance of compatibility and effectiveness
- highly active and broadly usable

APPLICATION RECOMMENDATION	
Brush application/roller application	
Airless spraying	
Compressed air spraying	
Flexo/gravure printing	
Dip coating, flow coating, curtain coating	
Flooring	

waterborne	solventborne
•	•
2-pack 100%	radiation-curing
•	•
addition to the grinding stage	addition to the let-down stage
•	•

TYPICAL APPLICATIONS

- Printing Inks
- General industrial coatings
- Wood coatings
- Others

TECHNICAL DATA

active matter content	100 %
appearance	clear to turbid liquid
chemical description	polyether siloxane copolymer, contains fumed silica
solvent	solvent-free

SOLUBILITY

Water	Ethanol
•	0
TPGDA	Butylacetate
•	•
Mineral Spirits	
•	

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.1 - 1.0 %

PROCESSING INSTRUCTIONS

- Stir before use
- Addition to the coating as supplied or as a predilution is possible.
- Long term effectiveness of the product is dependent on the formulation and should be tested in individual formulations.

HANDLING & STORAGE

When stored in an original unopened packaging between -10 and +40 °C, the product has a shelf life of 24 months from the date of manufacture.

MSDS & REGULATORY INFORMATION



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com

