

PEBAX® MH 2030

Polyether block amide Pebax® MH 2030 is a thermoplastic elastomer made of flexible polyether and rigid polyamide. Pebax® MH 2030 is an inherently dissipative polymer and can be dry blended or compounded with a polymer matrix to lower the surface resistivity of the final part.

MAIN CHARACTERISTICS

Property	Typical Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Water Absorption at Equilibrium At 20°C and 50 % R.H.	4.5	%	ISO 62
Water Absorption At 23°C and 24 h in water	120	%	
Melting Point	200	°C	ISO 11357
Hardness (*) Instantaneous	40	Shore D	ISO 868
Flexural Modulus (*)	80	MPa	ISO 178
Surface Resistivity (*)	1 10 ⁷	Ω / sq	IEC 60093
Volume Resistivity (*)	1 10 ⁷	Ω.cm	IEC 60093
Charge Decay Time (*)	< 1	s	MIL B-81705
Refractive Index	1.508	-	Internal method

(*) Samples conditioned 15 days at 23°C - 50 % R.H.

PEBAX® MH 2030

MAIN APPLICATIONS

- Permanent antistatic additive.

PROCESSING CONDITIONS

Conditions	Typical values
Extrusion Melt Temperature (Min / Recommended / Max)	230°C / 250°C / 280°C
Injection Melt Temperature (Min / Recommended / Max)	230°C / 240°C / 260°C
Mold Temperature	25 – 60°C
Drying (only necessary for bags opened for more than two hours) Time Temperature	5 - 7 hours 70 - 90°C

PACKAGING

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See Safety Data Sheet for Health & Safety Considerations.