

# Dynasytan® HYDROSIL 1151

## Aqueous 3-aminopropylsilane hydrolysate

### Technical data

Properties and test methods	Value	Unit	Method
Refractive index n(20,D)	approx. 1.371	-	DIN 51423
Viscosity (20 °C)	approx. 3.7	mPa·s	DIN 53015
pH (20 °C, 1:1 in H <sub>2</sub> O)	10-12	-	DIN 19268
Density (20 °C)	approx. 1.06	g/cm <sup>3</sup>	DIN 51757
Flash point	approx. 80	°C	EN 22719

### Registrations

#### Dynasytan® HYDROSIL 1151

DSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	Yes
EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
REACH (Europe)	Exempted

Dynasytan® HYDROSIL 1151 is an amino-functional silane which acts as an adhesion promoter between inorganic materials (for example glass, metals and fillers) and organic polymers (thermosets, thermoplastics and elastomers).

Dynasytan® HYDROSIL 1151 is a colorless to slightly yellowish aqueous solution with an amine-like odor, miscible, with alcohols or water. Dynasytan® HYDROSIL 1151 contains about 40% active silane content in water.

### Safety and handling

Before considering the use of Dynasytan® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website [www.dynasytan.com](http://www.dynasytan.com) or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

### Packaging, storage and shelf life

Dynasytan® HYDROSIL 1151 is supplied in 25 kg and 200 kg drums and 1.000 kg bulk containers.

In the originally sealed drum Dynasytan® HYDROSIL 1151 has a shelf life of min. 12 months from delivery. It is recommended to store Dynasytan® HYDROSIL 1151 above freezing temperatures.

Singular freezing does not influence the product quality. Frozen product is re-useable after complete thawing and homogenizing (accurate stirring is sufficient).

## Properties and applications

Dynasylan® HYDROSIL 1151 is an important additive in many applications. Particular advantages arise in water-based systems.

Examples:

- glass fibre/glass fabric composites: as size constituent or finish
- glass and metal primers
- mineral fibre insulating materials, abrasives: as additive to phenolic resin binders
- foundry resins: as an additive to cold-curing phenolic and furane resins
- sealants and adhesives: as primer or additive mineral-filled composites: for pretreatment of fillers and pigments or as additive
- paints and coatings: as additive and primer for improving adhesion to the substrate.

The most important effects which can be achieved using Dynasylan® HYDROSIL 1151 are: improvement in product properties, such as

- mechanical properties, for example flexural strength, tensile strength, impact strength and modulus of elasticity
- moisture and corrosion resistance

improvement in processing properties, such as

- adhesion
- better filler dispersion
- high flash point

## Reactivity

Dynasylan® HYDROSIL 1151 is a bifunctional organic compound in which the functional silanol groups can be bonded to an inorganic substrate; the organophilic amino group can interact with a suitable polymer. The particular advantage of Dynasylan® HYDROSIL 1151 compared with the corresponding aminofunctional alkoxy silanes is its nonflammability, the fact that no volatile organic constituents are released and the fact that no particular equipment safety precautions are necessary. Dynasylan® HYDROSIL 1151 can be diluted with water in all proportions. The hydrolysates are long-term stable.

Examples of suitable inorganic substrates are glass, glass fibres, glass wool, mineral wool, silicic acid, quartz, sand, cristobalite, wollastonite and mica; also suitable are aluminium trihydroxide, kaolin, talc, other silicate fillers, metal oxides and metals. Examples of particularly suitable polymers are epoxy resins, polyurethanes, phenolic resins, furane resins, melamine resins, PA, PBT, PC, EVA, PP, PVAC, acrylates and silicone.

## Processing

Dynasylan® HYDROSIL 1151 can be applied advantageously in water-based binder systems or for substrate pretreatment. It can also be used as a constituent of aqueous sizes or as an additive.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Europe/Middle-East/Africa/RoW**  
**Evonik Resource Efficiency GmbH**

Business Line Silanes  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 13636  
FAX +49 6181 59 713915  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik (SEA) Pte. Ltd.**

Business Line Silanes  
3 Internatioanl Business Park  
#07-18, Nordic European Centre  
Singapore 609927  
PHONE +65 6809 6576  
FAX +65 6809 6699  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Japan Co. Ltd**

Business Line Silanes  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7446  
FAX +81 353 23 7397  
dynasytan@evonik.com  
www.dynasytan.com

**North America**

**Evonik Corporation**

Business Line Silanes  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE (TOLL FREE) +1 800 237 67 45  
PHONE +1 973 929 8513  
FAX +1 973 929 8503  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Specialty**

**Chemicals (Shanghai) Co. Ltd.**

Business Line Silanes  
55, Chungdong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 61191-399  
FAX +86 21 61191-648  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik India Pvt. Ltd.**

Business Line Silanes  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
dynasytan@evonik.com  
www.dynasytan.com

**North America**

**Silbond Corporation**

9901 Sand Creek Highway  
Weston, MI 49289  
USA  
PHONE +1 517 436 9316  
FAX +1 517 436 3148  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Korea Ltd.**

Business Line Silanes  
94, Galsan 1-dong  
Bupyeong-gu  
Incheon, 403-081  
Korea  
PHONE +82 2320 4773  
FAX +82 2783 2520  
dynasytan@evonik.com  
www.dynasytan.com

**Latin America**

**Evonik Brasil Ltda.**

Business Line Silanes  
Alameda Campinas, 579  
01404-000 São Paulo-SP  
Brazil  
PHONE +55 11 3146 4123  
FAX +55 11 3146 4148  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Taiwan Ltd.**

Business Line Silanes  
Artist Construction Bldg.  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan 10596  
PHONE +886 227 17 1242  
FAX +886 227 17 2106  
dynasytan@evonik.com  
www.dynasytan.com