

TEGO® Airex 931**DESCRIPTION**

TEGO® Airex 931 shows high efficiency in combination with good compatibility. First choice in case of foam stabilization. Suitable for a broad range of coating systems.

KEY BENEFITS

- universal use in clear and pigmented formulations
- for solventborne coatings
- highly efficient with good compatibility

APPLICATION RECOMMENDATION**Brush application/roller application****Airless spraying****Compressed air spraying****Flexo/gravure printing****Dip coating, flow coating, curtain coating****Flooring****SUITABILITY****waterborne****solventborne****2-pack 100%****radiation-curing****pigmented coatings****clear coatings**

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Wood coatings
- General industrial coatings
- Floor coatings
- Protective coatings

TECHNICAL DATA

active matter content	approx. 1 %
appearance	clear liquid
chemical description	solution of a fluorosilicone
solvent	diisobutylketone

SOLUBILITY

Water	Ethanol
●	●
TPGDA	Acetone
●	●
Butylacetate	Mineral Spirits
●	●

● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.1 - 1.0 %

PROCESSING INSTRUCTIONS

- Stir before use!
- Addition may be either in the grind or during the let-down procedure.
- Addition as supplied is recommended.

HANDLING & STORAGE

When stored in an original unopened packaging between -40 and +40 °C, the product has a shelf life of at least 36 months from the date of manufacture.

MSDS & REGULATORY INFORMATION

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Resource Efficiency GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com