

EBECRYL® 4175

Hard unsaturated wax-free polyester resin

INTRODUCTION

Ebecryl®4175 is a hard unsaturated wax-free polyester resin recommended for use in cost-effective UV-curing primers and coatings for wood.

Ebecryl®4175 is diluted with 25% dipropylene glycol diacrylate (DPGDA)

PERFORMANCE DATA

Formulations based on Ebecryl®4175 are recommended for:

- UV and EB cured roller primers and coatings
- curtain coater applied coatings for wood, cork and furniture.

SUGGESTED APPLICATIONS

Ebecryl®4175 is used in formulation of radiation-curing (UV and EB) coating for application by roller coating, spraying and curtain coating on wood, cork and furniture.

Ebecryl®4175 can be used to formulate clear high-gloss to matt UV-curing systems.

SPECIFICATIONS

Viscosity at 23°C, mPa.s	17000±2000
Haze colour value	max 200

GENERAL PROPERTIES

Acid number, mg KOH/g	20 ±3
Density, g/cm ³	approx 1.15
Flash point °C	>100

COMPATIBILITY

Generally speaking, Ebecryl®4175 is compatible with other acrylic monomers and oligomers. However, the compatibility should always be tested, especially with respect to the addition of other resins and additives.

SOLUBILITY

Toluene, Xylene	Partly soluble
Aliphatic hydrocarbons	Insoluble
Alcohols	Partly soluble
Esters	Soluble
Ketones	Soluble

SUGGESTED FORMULATIONS

Ebecryl®4175 can be used to formulate clear high-gloss to matt UV-curing systems. The amount of photoinitiator added depends on the reactivity required and on the acrylic monomer or oligomer used to adjust the viscosity of the system.

For roller coating at a thickness of approx. 40µm, for example, DPGDA can be used to adjust the viscosity to approx 2000mPa.s. Afterwards 5% PI is added, calculated on the polymerisable substance, to give a belt speed of approx. 7m/min under an 80Watt lamp.

This results in a film with good hardness and high gloss. To achieve matting effects, we recommend trial with Gasil® HP240 (Crosfiled) or Syloid®ED products (Grace).

STORAGE AND HANDLING

Storage in original sealed Allnex containers.

Recommended storage temperature : -5 to + 35°C

Protect from intense radiation (light, UV), heat and foreign material.

Allnex guarantees that for a period of 24 months following the day of manufacturing, the product will meet the specifications or values set forth in section "specifications or characteristic data" above, whatever is applicable, provided that the product is stored in full compliance with the storage conditions set forth

in and referenced under section “storage” above and is otherwise handled appropriately.

The lapse of the 24 months period does not necessarily mean that the product no longer meets specifications or the set values. However, prior to using said product, Allnex recommend to test such a product if it still meets the specifications or the set values. Allnex does not make any guarantees regarding the product after the lapse of the 24 months period and Allnex shall not be responsible or liable in any way for the product failing to meet specifications or the set values after the lapse of the 24 months period.

STATUTORY LABELLING

For Statutory Labelling information, please refer to Safety Data Sheet.

DPGDA is produced by Allnex

June 2015

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies (“Allnex”) decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex’s best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.