

EBECRYL® 4654

Aliphatic Urethane Acrylate

March 2017



INTRODUCTION

EBECRYL 4654 is an aliphatic urethane acrylate supplied at 60% solids in n-butyl acetate. Films of EBECRYL 4654 are physically dry after evaporation of the solvent. EBECRYL 4654 exhibits high reactivity in ultraviolet (UV) and electron beam (EB) energy curable coatings and yields hard polymers. Coatings based on EBECRYL 4654 demonstrate good exterior durability, resistance to yellowing, and chemical and mechanical resistance properties.

PERFORMANCE HIGHLIGHTS

UV/EB cured coatings based on EBECRYL 4654 are characterized by the following performance properties:

- Physically dry after solvent evaporation
- Good chemical and mechanical resistance properties
- High resistance to yellowing and exterior durability

The actual properties of UV/EB energy cured products also depend on the selection of other formulation components such as reactive diluents, additives and photoinitiators.

SUGGESTED APPLICATIONS

EBECRYL 4654 is designed for use in the formulation of UV/EB energy cured coatings for automotive clear coats by spray application.

FORMULATING

Depending on the application, the coating can be adjusted to the appropriate viscosity using standard reactive diluents such as dipropylene glycol diacrylate (DPGDA)⁽¹⁾, 1,6-hexanediol diacrylate (HDDA)⁽¹⁾, isobornyl acrylate (IBOA)⁽¹⁾, and trimethylolpropane triacrylate (TMPTA)⁽¹⁾ or solvents such as butyl acetate.

The reactive diluent must be selected carefully as it may impact considerably on the properties and storage stability of the coating. Because of the many potential combinations with reactive diluents and solvents compatibility must be tested in each individual case.

UV curing of coatings formulated with EBECRYL 4654 requires the addition of standard commercial photoinitiators. Typical levels are 4-6%, though this may vary to meet the reactivity requirements of the application. In the case of EB curing, a low oxygen atmosphere must be ensured to avoid surface inhibition.

TYPICAL PHYSICAL PROPERTIES

	VALUE
Acid number, mg KOH/g	1
Color, Pt-Co scale ⁽²⁾	100
Density, g/ml at 20°C	1.02
Flash point, °C	72
Solvent content, n-butyl acetate	40%
Viscosity, 23°C, cP/mPa·s	750

PRECAUTIONS

Before using EBECRYL 4654, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

EBECRYL 4654 contains a flammable or combustible liquid and vapor. Consult the SDS for additional storage and handling recommendations.

See the SDS for the recommended storage temperature range for EBECRYL 4654.

Please refer to the allnex Guide to Safety and Handling of Acrylate Oligomers and Monomers for additional information on the safe handling of acrylates.

(1) Product of allnex

(2) Also referred to as APHA/Hazen color

www.allnex.com

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.