


β-CEA

β-Carboxyethyl Acrylate

February 2017



average n = 1

INTRODUCTION

β-carboxyethyl acrylate (β-CEA) is a mixture of reactive esters, each of which contain both acrylate and carboxylic acid functionality in the same molecule. Referring to the included structural formula, this mixture contains some unreacted acrylic acid (n=0), along with higher adducts of acrylic acid (n=1,2,3...). The dimer (n=1), i.e. β-CEA, is the largest single component, and the average molecular weight is equivalent to that of the dimer. β-CEA will polymerize when exposed to sources of free radicals. Because of its carboxylic acid functionality, β-CEA is useful as an adhesion promoter.

PERFORMANCE HIGHLIGHTS

β-CEA is characterized by:

- Low color
- Moderate viscosity

UV/EB curable formulated products containing β-CEA are characterized by:

- Good adhesion to a variety of substrates
- Low Tg

The actual properties of UV/EB cured products also depend on the selection of other formulation components such as oligomers, additives and photoinitiators.

SUGGESTED APPLICATIONS

β-CEA is a diluent compatible with a wide range of acrylates used in UV/EB curing applications. Good adhesion to many different substrates makes β-CEA useful in a variety of overprint varnishes, inks, and coatings.

SPECIFICATIONS

	VALUES
Acid value, meq KOH/g	6.10-6.70
Acid value, mg KOH/g	342.2-375.9
Appearance	Clear liquid
Color, Pt-Co scale ⁽¹⁾ , max.	200
Ester rank, meq KOH/g	6.40-7.00
Inhibitor (MEHQ), ppm	900-1100
Viscosity, 25°C, cP/mPa-s	70-100
Water, wt. %, max.	1.000

TYPICAL PHYSICAL PROPERTIES

Density, g/ml at 25°C	1.21
Flash point, °C	87
Melting point, °C	<-35
Molecular weight, theoretical average	144

CHEMICAL ABSTRACT SERVICE NUMBER

24615-84-7

2-Propenoic acid, 2-carboxyethyl ester

PRECAUTIONS

Before using β-CEA, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

See the SDS for the recommended storage temperature range for β-CEA.

Please refer to the allnex Guide to Safety and Handling of Acrylate Oligomers and Monomers for additional information on the safe handling of acrylates.

(1) Also referred to as APHA color.

www.allnex.com

Disclaimer: allnex Group companies ('allnex') decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.