

CYMEL[®] 327 resin

April 2020



PRODUCT DESCRIPTION

CYMEL 327 resin is a methylated high imino melamine crosslinker supplied in iso-butanol. CYMEL 327 resin is very reactive and has a tendency towards self-condensation at normal baking temperatures, providing films with very good hardness, gloss, chemical resistance and outdoor durability. Its major advantage relative to other high imino resins is its potential to lower VOC in high solids formulations.

BENEFITS

- High solids
- Fast cure response
- Low formaldehyde release

APPLICATION AREAS

- High solids coatings
- Waterborne coatings
- Coil coatings and metal decorating
- Automotive coatings

PHYSICAL PROPERTIES

Property	Range	Method
Appearance	Clear Liquid	ASTM E284
Non-volatile by wt.	88-92%	DIN 55671 (Foil, 45 min/45°C)
Viscosity, 23°C	5100-16000 mPa·s	DIN EN ISO 3219
Free formaldehyde	< 0.5 %	BS-EN-1243-2011
Color, APHA	≤ 50	DIN EN ISO 6271

TYPICAL PROPERTIES (NOT CONTINUALLY MEASURED)

Property	Range	Method
Density, 23°C	9.7 – 9.9 lbs/gal	ASTM D1475-13

SOLUBILITY

Alcohols	Complete
Esters	Complete
Ketones	Complete
Aromatic hydrocarbons	Partial
Aliphatic hydrocarbons	Insoluble
Water	Complete

COMPATIBILITY

Acrylic resins	Very good
Alkyd resins	Very good
Epoxy resins	Very good
Polyester resins	Very good

BACKBONE POLYMER SELECTION

CYMEL 327 resin is an effective crosslinker for backbone polymer resins containing hydroxyl, carboxyl, and amide functional groups, such as those found on alkyd, polyester or acrylic resins. Although the optimum level of CYMEL 327 resin should be determined experimentally, ratios of 25 to 35% based on resin solids are typically most effective.

CATALYSIS

CYMEL 327 resin may not require the addition of an acid catalyst to the formulation to obtain effective cure. In many instances, the acidity of the backbone polymer in the formulation is sufficient to catalyze the reaction under normal baking conditions (15-20 minutes at 120-150°C). If catalyst addition is required, then 0.5-1.0% of CYCAT[®] 296-9 catalyst based on total resin solids is recommended.

FORMULATION STABILITY

The stability of solvent-borne systems containing CYMEL 327 resin can be enhanced by the addition of primary alcohols, amines, or a combination of these. Low molecular weight primary alcohols such as ethanol or n-butanol are most effective. Recommended amines are tertiary types, such as triethylamine or dimethylethanolamine, at a concentration of 0.5-1.0% on total binder solids. For best stability in waterborne systems, a pH of 7.5-8.5 should be maintained using tertiary amines only.

STORAGE STABILITY

CYMEL 327 resin has a shelf life of 720 days from the date of manufacture when stored at temperatures below 32°C. Although low temperatures are not detrimental to stability, its viscosity will increase, possibly making the resin difficult to pump or pour. The viscosity will reduce again on warming, but care should be taken to avoid excessive local heat as this can cause an irreversible increase in viscosity.

www.allnex.com

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with [®], [™] or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.