



D.E.R.[™] 325

Liquid Epoxy Resin

Description

D.E.R.[™] 325 Liquid Epoxy Resin is a mono-functional reactive diluent modified reaction product of epichlorohydrin with bisphenol-A.

Introduction

D.E.R. 325 Liquid Epoxy Resin is a low viscosity, C₁₂-C₁₄ aliphatic glycidyl ether diluted standard bisphenol-A based liquid epoxy resin. Its surface tension is lower than other reactive diluent diluted epoxy resins and results in better surface wetting, better adhesion, and will have slightly lower viscosity at any given filler loading. The lower surface tension also results in better filler acceptance, reduced odor, lower vapor pressure, and less potential for handling hazards.

The reactive diluent in this epoxy resin blend will increase the pot-life as well as the flexibility (impact resistance). The reactive diluent also limits the solvent resistance somewhat. D.E.R. 325 Epoxy Resin offers improved acid resistance versus standard epoxy resins such as D.E.R.[™] 331[™] Liquid Epoxy Resin.

A wide variety of curing agents is available to cure this liquid epoxy resin at ambient conditions. Most frequently used are cycloaliphatic polyamines, polyamides, amidoamines, and modified versions of these. Such systems are sometimes cured at elevated temperatures to improve selected properties such as chemical resistance and glass transition temperature. Elevated temperature cures are necessary and long post-cures are required to develop full end properties if anhydride or catalytic curing agents are employed.

NOTE: D.E.R. 325 Epoxy Resin might crystallize. This reversible physical phenomenon can be greatly avoided by storing the resin at temperatures not below 25°C. For further details see the technical bulletin, *Crystallization of Liquid Epoxy Resins*, Form No. 296-01652.

Typical Applications

This product is suitable for use in applications such as:

- Adhesives
- Casting and Tooling
- Civil Engineering
- Composites
- Marine and Protective Coatings
- Potting and Encapsulation

Typical Properties

Property ⁽¹⁾	Value	Method
Epoxide Equivalent Weight (g/eq)	185 – 206	ASTM D-1652
Epoxide Percentage (%)	20.9 – 23.2	ASTM D-1652
Epoxide Group Content (mmol/kg)	4850 – 5410	ASTM D-1652
Color (Platinum Cobalt)	125 Max.	ASTM D-1209
Viscosity @ 25°C (mPa·s)	850 – 2800	ASTM D-445
Density @ 25°C (g/ml)	1.10	ASTM D-4052
Shelf Life (Months)	24	

(1) Typical properties, not to be construed as specifications.

Safety and Handling

The Dow Chemical Company provides its customers with a product specific Material Safety Data Sheet (MSDS) or Safety Data Sheet (SDS) to cover potential health effects, safe handling, storage, use and disposal information. Dow strongly encourages its customers to review the MSDS or SDS on its products and other materials prior to their use.

D.E.R.™ 325 Liquid Epoxy Resin is supplied in bulk or in 225 kg tight-head drums. The resin should be stored in dry place in its original closed packaging. D.E.R. 325 Epoxy Resin should retain its chemical properties for a period of at least 24 months.

For further handling information consult the Dow brochure entitled, *DOW Epoxy Resins Product Stewardship Manual, Safe Handling and Storage*, Form No. 296-00312 and the technical bulletin, *Product Coding, Shelf-life and Storage Stability*, Form no. 296-01657.

NOTE: D.E.R. 325 Liquid Epoxy Resin can crystallize. This reversible, physical phenomena can be greatly avoided by storing the resin at temperatures not below 25°C. For additional information also consult the technical bulletin, *Crystallization of Liquid Epoxy Resins*, Form No. 296-01652.

Product Stewardship

The Dow Chemical Company has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis of our Product Stewardship philosophy by which we assess the health and environmental information on our products and then take the appropriate steps to protect employee and public health and the environment. The Dow Chemical Company has enduring commitments to Responsible Care® in the management of chemicals worldwide. Our Product Stewardship program rests with every individual involved with Dow products from the initial concept and research to the manufacture, sale, distribution, and disposal of each product.

Customer Notice

Dow encourages its customers and potential users of Dow products to review their applications for such products from the standpoint of human health and environmental quality. To help ensure that Dow products are not used in ways for which they were not intended or tested, Dow personnel are available to assist customers in dealing with ecological and product safety considerations. Your Dow sales representative can arrange for the proper contacts. Dow literature, including MSDS or SDS, should be consulted prior to the use of Dow products.

Medical Application Policy

Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- (a) permanent (long term) contact with internal body fluids or internal body tissues. Long term is a use which exceeds 72 continuous hours (except 30 days for PELLETHANE™ Polyurethane Elastomers);
- (b) use in cardiac prosthetic devices regardless of the length of time involved (cardiac prosthetic devices include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems and ventricular bypass assisted devices);
- (c) use as a critical component in medical devices that support or sustain human life; or
- (d) use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Additionally, all Products intended for use in pharmaceutical applications must pass the then current Pharmaceutical Liability Guidelines. For additional information please contact your regular Dow representative.

™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

® Responsible Care is a service mark of The American Chemistry Council in the United States

D.E.R. 325 Liquid Epoxy Resin

Form No. 296-01536-0506X-TD

Food Contact Applications

When properly formulated and cured for food contact applications, this resin will comply with the U.S. Food, Drugs and Cosmetics Act as amended under Food Additive Regulation 21 CFR 175.300 (b)(3)(viii)(a); "Epoxy resins, as basic polymer", for use only in coatings that are intended for contact with dry bulk food at room temperature. This use is also subject to good manufacturing practices and any limitations specified in each regulation. Please consult the regulations for complete details.

If your applications include food contact requirements, please contact your Dow representative for further information and forthcoming EC regulations. Also consult the Dow data sheet, *Food Additive Status for Epoxy Resins, Curing Agents and Epoxy Novolac Resins*, Form No. 296-01425.

Regulatory Status

The base epoxy resin component of this epoxy resin blend is regarded as a polymer according to the 6th Amendment of Council Directive 67/548/EEC and as substances according to Council Directive 92/32/EEC of 30 April 1992; the 7th Amendment of that same directive. This substance has been reported to the EC Commission as No-Longer Polymer (NLP), is registered under NLP # 500-033-5 and is, therefore, exempt from the European Inventory of Existing Chemical Substances (EINECS). In addition, Dow confirms that the chemicals and intentional additives which form the basis of this product are listed on EINECS.

The reactive diluent used in this resin; C₁₂-C₁₄ alkyl glycidyl ether (CAS registration number 68609-97-2), is listed under number 271-846-8 on EINECS.

For more information on the regulatory status of this product, please refer to the MSDS or SDS for this product.

Chemical Inventory Listing

CAS Number ⁽¹⁾		25085-99-8 / 68609-97-2
Europe	EINECS	NLP # 500-033-5 / 271-846-8
United States	TSCA	25085-99-8 / 68609-97-2
Canada	DSL	25085-99-8 / 68609-97-2
Australia	AICS	25085-99-8 / 68609-97-2
Japan	ENCS	7-1279 / 2-2426
Korea	KECL	KE-24083 / KE-27545
Philippines	PICCS	25085-99-8 / 68609-97-2
China	SEPA	25085-99-8 / 68609-97-2

(1) Please refer to the MSDS or SDS for this product to ensure this CAS number is consistent with the product(s) you use.

Contact information:

North America: 800-441-4369
+1-989-832-1426
+1-989-832-1465 (fax)
Mexico: +1-800-441-4369
Brazil: +55-11-5188-9222
+55-11-5188-9749 (fax)
Europe: +800-3-694-6367
+32-3-450-2240
+32-3-450-2815 (fax)
Asia Pacific: +800-7776-7776#
+800-7779-7779# (fax)
+60-3-7958-3392
+60-3-7958-5598 (fax)

except Indonesia and Vietnam

<http://www.dowepoxy.com>

Notice: No freedom from any patent owned by Dow or others is to be inferred. Dow assumes no obligation or liability for the information in this document. The information provided herein is presented in good faith and is based on the best of Dow's knowledge, information, and belief. Since use conditions at non-Dow facilities are beyond Dow's control and governmental regulations may differ from one location to another and may change with time, it is solely the Buyer's responsibility to determine whether Dow's products are appropriate for the Buyer's use, and to assure the Buyer's workplace, use, and disposal practices are in compliance with laws, regulations, ordinances, and other governmental enactments applicable in the jurisdiction(s) having authority over Buyer's operations. Consequently, Dow assumes no obligation or liability for use of these materials and makes no warranty, express or implied. The user of the information provided is solely responsible for compliance with any applicable federal, state, provincial, and local laws. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

