

## Product Information: *ExCal® CW Calcium Carbonate Medium Grades*

Cimbar Resources, Inc. ExCal® CW Calcium Carbonate products are processed from a high-purity ore to exacting specifications at our Houston, TX plant. These grades are processed for use in plastics, rubber, coatings, adhesives, sealants, mastics, and other specialty applications where color, binder demand and economics are of importance. These products are available in **50 lb. bags, 2,000 lb. bulk bags and bulk trucks.**

### Typical Chemical Properties

Parameter	Wt., %
CaCO <sub>3</sub>	98.0
MgCO <sub>3</sub>	0.8
Fe <sub>2</sub> O <sub>3</sub>	0.05
SiO <sub>2</sub>	<0.01
Al <sub>2</sub> O <sub>3</sub>	0.95
R <sub>2</sub> O <sub>3</sub>	0.1

### Typical Physical Properties

	ExCal® CW 100	ExCal® CW 200	ExCal® CW 325
*Color	95	95	96
% Passing 200 Mesh	70	-	-
% Passing 325 Mesh	-	84	97
Median Particle Size	-	-	14
pH	7 - 8	7 - 8	7 - 8
Specific Gravity	2.7	2.7	2.7
% Moisture	0.1	0.1	0.1
Oil Absorption	-	-	14
Acid Solubility	98	98	98
Bulk Density, lb/cu ft			
Loose	63	58	53
Packed	100	95	88

All statements, technical information and recommendations are based on tests we believe to be reliable, the accuracy or completeness is not guaranteed, and the following is made in place of all warranties, expressed or implied. Our only obligation is to replace product proved to be defective. We shall not be liable for any injury, loss or damage, direct or indirect, from using or not being able to use the product. Before using, customer must determine suitability of the product for the intended use and customer assumes the responsibility. Because the conditions of use of this product is beyond seller's control the product is sold without warranty either expressed or implied and upon condition that the purchaser make its own tests to determine suitability for purchaser's applications. Purchaser assumes all risks. No warranty is expressed or implied regarding the accuracy of this data, the results to be obtained from the use thereof, or that any such will not infringe on any patent. Data on this sheet is furnished on the condition that the person receiving it shall make his own tests to determine the suitability thereof, for his particular purpose. In addition, since we cannot anticipate or control the many different conditions under which this information may be used, we do not guarantee the applicability or accuracy of this information or its suitability in any situation.