

ORGALLOY®

EM 067 HSP

Orgalloy® EM 067 HSP resin is a flexible polyamide designed to be used for refrigerant barrier layer in air conditioning rubber hose.

Packaging:

This grade is delivered dried in sealed packaging (20kg bags) ready to be processed.

Shelf life:

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	1 / *	cm ³ /10min	ISO 1133
Temperature	235 / *	°C	-
Load	5 / *	kg	-
MECHANICAL PROPERTIES			
Tensile Modulus	- / 572	MPa	ISO 527-1/-2
Stress at 50% Strain	- / 32	MPa	ISO 527-1/-2
Strain at Break	- / >50	%	ISO 527-1/-2
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	215 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1140 / 1140	kg/m ³	ISO 1183

Processing conditions:

- Drying time (only necessary for bags opened for more than two hours): 4-16 hours at 80-90°C
- Extrusion melt temperature (min-recommended-max): 240-260-300°C

PROCESSING

Film Extrusion, Profile Extrusion, Other Extrusion

DELIVERY FORM

Pellets

ADDITIVES

Plasticizer

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Orgalloy® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

ARKEMA