

# EBECRYL<sup>®</sup> 4266

## INTRODUCTION

Ebecryl<sup>®</sup>4266 is a Unsaturated aromatic epoxy acrylate. In the formulation of UV-curing and EB coatings. Without reactive thinner.

## PERFORMANCE DATA

Coatings based on Ebecryl<sup>®</sup>4266 are characterized by their good sandability and high abrasion resistance. Being an aromatic epoxy acrylate, the product is characterized by its good balance of hardness and flexibility.

## SUGGESTED APPLICATIONS

Ebecryl<sup>®</sup>4266 is used in the formulation of radiation-cured (UV and electron beam) coatings for application by roller coating, spraying and curtain coating on wood, cork, furniture, paper, parquet and film. Depending on the application, the coating can be adjusted to application viscosity using conventional reactive thinners (mono-, di-, tri- or tetraacrylates) or solvents such as butyl acetate. The low viscosity of the supply form means that less reactive thinner is required and the binder properties are thus retained over a wide viscosity range.

## CHARACTERISTIC DATA

Viscosity at 23°C, mPa.s	4500 - 8500
Iodine colour value	Max 4
Acid value	Max 2

## GENERAL PROPERTIES

Density, g/cm <sup>3</sup>	approx 1.14
Flash point	> 100
Hydroxyl content	approx. 1.8%

## COMPATIBILITY

On account of the many possible combinations with other resins, thinners and additives, the compatibility must always be tested.

## SUGGESTED FORMULATIONS

Thinning with alkoxyated tri- or tetraacrylates in the ratio 7 : 3 to 6 : 4 produces viscosities suitable for application by rolling coating. In the case of combinations of Ebecryl<sup>®</sup>4266with polyisocyanates (dual cure), particular attention should be given to the pot life.

Because of the many potential combinations with thinners, solvents or other substances, compatibility must be tested in each individual case. UV curing of coatings formulated with Ebecryl<sup>®</sup>4266requires the addition of conventional photoinitiators. Up to 5 % is added or concentrations which meet the reactivity requirements of the application. In the case of electron beam curing, good inertisation must be ensured (risk of surface inhibition).

Matt coatings can be produced using conventional matting agents. Care should be taken with respect to sedimentation which may cause the coating to gel prematurely.

## STORAGE AND HANDLING

Storage in original sealed Allnex containers.  
Recommended storage temperature: -10°C to 35°C  
Protect from intense radiation (light, UV), heat and foreign material.

Product is sensitive to moisture, skinning may occur in opened container.

Allnex guarantees that for a period of 24 months following the day of manufacturing, the product will meet the specifications or values set forth in section "specifications or characteristic data" above, whatever is applicable, provided that the product is stored in full compliance with the storage conditions set forth

In and referenced under section "storage" above and is otherwise handle appropriately.

The lapse of the 24 months period does not necessarily mean that the product no longer meets specifications or the set values. However, prior to using said product, Allnex recommend to test such a product if it still meets the specifications or the set values. Allnex does not make any representation regarding the product after the lapse of the 24 months

period and Allnex shall not be responsible or liable in any way for the product failing to meet specifications or the set values after the lapse of the 24 months period.

## STATUTORY LABELLING

---

For Statutory Labelling information, please refer to Safety Data Sheet.

June2015

---

• Worldwide Contact Info: [www.allnex.com](http://www.allnex.com) •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with the ®, ™ or \* are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.