



## D.E.R.™ 660-B80

Epoxy Resin Solution

### Description

D.E.R.™ 660-B80 Epoxy Resin Solution is a semi-solid reaction product of epichlorohydrin and bisphenol-A dissolved in n-butanol.

### Introduction

D.E.R. 660-B80 Epoxy Resin Solution is an intermediate epoxy equivalent weight epoxy resin dissolved in butanol, and is used mainly in adhesives and protective coatings, or as a modifier for other epoxy resins to improve impact strength, extensibility, and adhesion.

This epoxy resin solution can provide the high solids and chemical resistance of liquid epoxy resins combined with the adhesion, flexibility, excellent mechanical properties, and fast cure of higher molecular weight 1-type solid epoxy resin solutions.

D.E.R. 660-B80 Epoxy Resin can form the basis of many two-component coating systems with either polyamine, polyamide or polyamidoamine curing agents to provide high quality coatings which are resistant to a number of chemical reagents. D.E.R. 660-B80 Epoxy Resin Solution is ideal for adhesives and medium to heavy duty coatings such as those used for ship hulls, marine paints, tank linings, and industrial maintenance coatings.

### Typical Applications

This product is suitable for use in applications such as:

- Adhesives
- Civil Engineering
- Marine and Protective Coatings

### Typical Properties

Property <sup>(1)</sup>	Value	Method
Epoxy Equivalent Weight on solids (g/eq)	300 – 350	ASTM D-1652
Epoxy Percentage on solids (%)	12.3 – 14.3	ASTM D-1652
Epoxy Group Content, on solids (mmol/kg)	2860 – 3340	ASTM D-1652
Color (Gardner)	3 Max.	ASTM D-1544
Viscosity @ 25°C (mPa·s)	2300 – 6200	ASTM D-445
Non-Volatile Content (wt%)	79 – 81	DowM 101188
Solvent	n-Butanol	
Shelf Life 23°C (Months)	12	

(1) Typical properties, not to be construed as specifications.

### Safety and Handling

The Dow Chemical Company provides its customers with a product specific Material Safety Data Sheet (MSDS) or Safety Data Sheet (SDS) to cover potential health effects, safe handling, storage, use and disposal information. Dow strongly encourages its customers to review the MSDS or SDS on its products and other materials prior to their use.

This solid epoxy resin solution is supplied in bulk or in 215 kg tight-head drums. The resin solution should be stored in a dry place in its original closed packaging. This low molecular weight solid epoxy resin solution should retain its chemical properties for a period of at least 12 months.

**Safety and Handling (continued)**

For further handling information consult the Dow brochure entitled, *DOW Epoxy Resins Product Stewardship Manual, Safe Handling and Storage*, Form No. 296-00312 and the Dow technical bulletin, *Product Coding, Shelf-life and Storage Stability*, Form No. 296-01657.

**Product Stewardship**

The Dow Chemical Company has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis of our Product Stewardship philosophy by which we assess the health and environmental information on our products and then take the appropriate steps to protect employee and public health and the environment. The Dow Chemical Company has enduring commitments to Responsible Care® in the management of chemicals worldwide. Our Product Stewardship program rests with every individual involved with Dow products from the initial concept and research to the manufacture, sale, distribution, and disposal of each product.

**Customer Notice**

Dow encourages its customers and potential users of Dow products to review their applications for such products from the standpoint of human health and environmental quality. To help ensure that Dow products are not used in ways for which they were not intended or tested, Dow personnel are available to assist customers in dealing with ecological and product safety considerations. Your Dow sales representative can arrange for the proper contacts. Dow literature, including MSDS or SDS, should be consulted prior to the use of Dow products.

**Medical Application Policy**

Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- (a) permanent (long term) contact with internal body fluids or internal body tissues. Long term is a use which exceeds 72 continuous hours (except 30 days for PELLETHANE™ Polyurethane Elastomers);
- (b) use in cardiac prosthetic devices regardless of the length of time involved (cardiac prosthetic devices include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems and ventricular bypass assisted devices);
- (c) use as a critical component in medical devices that support or sustain human life; or
- (d) use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Additionally, all Products intended for use in pharmaceutical applications must pass the then current Pharmaceutical Liability Guidelines. For additional information please contact your regular Dow representative.

**Food Contact Applications**

When properly formulated and cured for food contact applications, this resin will comply with the U.S. Food, Drugs and Cosmetics Act as amended under Food Additive Regulation 21 CFR 175.300. This use is also subject to good manufacturing practices and any limitations specified in each regulation. Please consult the regulations for complete details.

If your applications include food contact requirements, please contact your Dow representative for further information and forthcoming EC regulations.

™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow  
® Responsible Care is a service mark of The American Chemistry Council in the United States  
D.E.R. 660-B80 Epoxy Resin Solution

## Regulatory Status

The base epoxy resin component of this epoxy resin solution is regarded as a polymer according to Council Directive 92/32/EEC of 30 April 1992; the 7<sup>th</sup> Amendment of Council Directive 67/548/EEC, and is, therefore, exempt from the European Inventory of Existing Chemical Substances (EINECS). In addition, Dow confirms that the chemicals and intentional additives which form the basis of this product are listed on EINECS.

The n-butanol solvent component (CAS registration number 71-36-3) in this epoxy resin solution is listed on EINECS under the registration number 200-751-6.

For more information on the regulatory status of this product, please refer to the MSDS or SDS for this product.

## Chemical Inventory Listing

CAS Number <sup>(1)</sup>		25036-25-3 / 71-36-3
Europe	EINECS	Polymer / 200-751-6
United States	TSCA	25036-25-3 / 71-36-3
Canada	DSL	25036-25-3 / 71-36-3
Australia	AICS	25036-25-3 / 71-36-3
Japan	ENCS	7-1279 / 2-3049
Korea	KECL	KE-24000 / KE-03867
Philippines	PICCS	25036-25-3 / 71-36-3
China	SEPA	25036-25-3 / 71-36-3

(1) Please refer to the MSDS or SDS for this product to ensure this CAS number is consistent with the product(s) you use.

### Contact information:

North America: 800-441-4369  
+1-989-832-1426  
+1-989-832-1465 (fax)  
Mexico: +1-800-441-4369  
Brazil: +55-11-5188-9222  
+55-11-5188-9749 (fax)  
Europe: +800-3-694-6367  
+32-3-450-2240  
+32-3-450-2815 (fax)  
Asia Pacific: +800-7776-7776#  
+800-7779-7779# (fax)  
+60-3-7958-3392  
+60-3-7958-5598 (fax)

# except Indonesia and Vietnam

<http://www.dowepoxy.com>

**Notice:** No freedom from any patent owned by Dow or others is to be inferred. Dow assumes no obligation or liability for the information in this document. The information provided herein is presented in good faith and is based on the best of Dow's knowledge, information, and belief. Since use conditions at non-Dow facilities are beyond Dow's control and governmental regulations may differ from one location to another and may change with time, it is solely the Buyer's responsibility to determine whether Dow's products are appropriate for the Buyer's use, and to assure the Buyer's workplace, use, and disposal practices are in compliance with laws, regulations, ordinances, and other governmental enactments applicable in the jurisdiction(s) having authority over Buyer's operations. Consequently, Dow assumes no obligation or liability for use of these materials and makes no warranty, express or implied. The user of the information provided is solely responsible for compliance with any applicable federal, state, provincial, and local laws. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

