




Description

ZHENGDA[®] ZT-1500 Polyether Amine

ZHENGDA[®] ZT-1500 Polyether Amine (also called Amine-terminated Polyether) is a trifunctional primary amine of approximately 5000 molecular weight. It is clear, almost colorless, viscous, liquid product.



- APPLICATIONS**
- Crosslinker for polyurea
 - Co-reactant in epoxy systems where adhesion promotion and flexibility are important
 - Surfactant and corrosion inhibitor applications

- BENEFITS**
- Low color
 - Increased peel strength in epoxy adhesives
 - Increased toughness

SALES SPECIFICATIONS

<u>Property</u>	<u>Specifications</u>
Appearance	Colorless to pale yellow liquid with slight haze permitted
Color, Pt-Co	25 max.
Primary amine, % of total amine	97 min.
Total amine, meq/g	0.5 – 0.57
Water, wt%	0.25 max.

ADDITIONAL INFORMATION

AHEW (Amine hydrogen equivalent wt.), g/eq	952	Flash point, PMCC, °C (°F)	213 (415)
Equivalent wt. with isocyanates, g/eq	1904	Density, g/ml (lb/gal) 25°C	0.997 (8.31)
Viscosity, cSt, 25°C (77°F)	819	CAS Number	64852-22-8

TOXICITY AND SAFETY

For additional information on the toxicity and safe handling of this product, consult the Material Safety Data Sheet (Safety Data Sheet in Europe) prior to use of this product.

HANDLING AND STORAGE

Materials of Construction

At temperatures of 75-100°F (34-38°C)

Tanks	Carbon steel
Lines, valves	Carbon steel
Pumps	Carbon steel
Heat exchange Surfaces	Stainless steel
Hoses	Stainless steel, polyethylene, polypropylene, and TEFLON®
Gaskets, packing	Polypropylene or TEFLON® (elastomers such as neoprene, Buna N, and VITON® should be avoided)
Atmosphere	Nitrogen or dry air

At temperatures above 100°F (38°C)

Tanks	Stainless steel or aluminum
Lines, Valves	Stainless steel
Pumps	Stainless steel or Carpenter 20 equivalent
Atmosphere	Nitrogen

ZHENGDA® ZT-1500 polyetheramine may be stored under air at ambient temperatures for extended periods. A nitrogen blanket is suggested for all storage, however, to reduce the effect of accidental exposure to high temperatures and to reduce the absorption of atmospheric moisture and carbon dioxide. It should be noted that pronounced discoloration is likely to occur at temperatures above 140°F (60°C), whatever the gaseous pad.

Cleanout of lines and equipment containing ZHENGDA ZT-1500 polyetheramine can be accomplished using warm water and steam. In the event of spillage of this product, the area may be flushed with water. The proper method for disposal of waste material is by incineration with strict observance of all federal, state, and local regulations.

AVAILABILITY

ZHENGDA ZT-1500 polyetheramine is available in tank cars, tank wagons, 55-gallon (208L) drums of 440 pounds (200kg) net weight, and 5-gallon (19L) cans.

Samples are available by contacting our office.

Main Offices : ZIBO ZHENGDA POLYURETHANE Co.,Ltd.

Add:RM 1904, ChuangYeHuoJuGuangChang E, Zhangdian, Zibo City, 255000, Shandong Province, P.R.China

Tel:0086-533-3146343

Fax:0086-533-3142021

E-mail: arnie@dexin-chem.com

www.china-polyol.com