

CYCAT[®] XK 406 N

TYPE

Acidic catalyst

FORM OF DELIVERY (f.o.d.)

Appearance

light to dark reddish coloured, low viscous liquid

SPECIAL PROPERTIES AND USE

CYCAT XK 406 N is a phosphoric acid derivate. CYCAT XK 406 N increases the crosslinking speed of heat curing coating systems based on e.g. phenolic/-epoxide resin combinations.

A significant improvement of adhesion properties is often seen in connection with the use of CYCAT XK 406 N.

Furthermore, the use of CYCAT XK 406 N often leads to an improved sulphur staining resistance of interior can coating systems based on phenolic/epoxide resin combinations.

PRODUCT DATA

Determined per batch:

Phosphoric acid Content VLN 303
content [%] 8,9 - 9,3

Iodine Colour Number DIN 6162
iodine colour number <= 50

Not continually determined:

Density (Liquids) DIN EN ISO 2811-2
density [g/cm³] approx. 0,90
(20 °C)

Flash Point DIN EN ISO 1523
flash point [°C] approx. 22

COMPATIBILITY

CYCAT 406 N is compatible with high molecular weight epoxide resins and most resoles used in such combinations. The Phenodur grades PR 285 and PR 373 are not compatible with CYCAT XK 406 N.

PROCESSING

For combinations of phenolic- and high molecular weight epoxide resins we recommend to add 2 - 5 % (calculated on solid resin).

Since phenolic resins are often combined with other coating raw materials, one should always find out the optimal content of CYCATI XK 406 N by trials. Overdosage of CYCAT XK 406 N has a negative influence onto the storage stability of the lacquers containing it.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

DISTIGUISHING FEATURES

CYCAT XK 406 N differs from Additol XK 406 only in that it does not contain white spirit as solvent.

U.S. Environmental Protection Agency restrictions and requirements

The importation, processing or use of this product in the United States of America is subject to a Significant New Use Rule (SNUR) issued by the U.S. Environmental Protection Agency (US EPA). Among other conditions, the SNUR prohibits the predictable or purposeful release of the product to waters of the U.S. from manufacturing, processing or uses and imposes certain notice and recordkeeping requirements. Please see 40 CFR 721.5905 [or 40 CFR 721.5908 as applicable] for further information. This product may also be subject to export notification under TSCA Sec. 12(b).

7.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.
© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.