

EBECRYL® 4740

Aliphatic Allophanate Urethane Acrylate

INTRODUCTION

EBECRYL 4740 is a weather-stable aliphatic urethane acrylate having a low viscosity due to the allophanate structure. Formulations based on EBECRYL 4740 exhibit high reactivity and yield tough and elastic polymers. Coatings formulated with EBECRYL 4740 are characterized by very good chemical and mechanical resistances, scratch resistance, abrasion resistance and high resistance to yellowing.

SUGGESTED APPLICATIONS

EBECRYL 4740 is used in the formulation of radiation-curing coatings (UV and electron beam) for the coating of wood, plastics and mineral substrates via the roller, spray and curtain coating processes. Due to the elastic properties of EBECRYL 4740 the product is especially suitable for coatings on flexible substrates or as an additional binder to modify the elasticity of radiation curing coatings.

FORMULATING

Depending on the application, the coating can be adjusted to the appropriate viscosity using standard reactive diluents such as dipropylene glycol diacrylate (DPGDA)⁽¹⁾, 1,6-hexanediol diacrylate (HDDA)⁽¹⁾, isobornyl acrylate (IBOA)⁽¹⁾, and trimethylolpropane triacrylate (TMPTA)⁽¹⁾ or solvents such as butyl acetate.

EBECRYL 4740 coating formulations require less reactive diluent and thus the binder properties are retained over a broad range of viscosities. Application at higher temperatures is also possible.

The reactive diluent must be selected carefully as it may impact considerably on the properties and storage stability of the coating. Because of the many potential combinations with reactive diluents and solvents compatibility must be tested in each individual case.

UV curing of coatings formulated with EBECRYL 4740 requires the addition of standard commercial photoinitiators. Typical levels are 4-6%, though this may vary to meet the reactivity requirements of the application. In the case of EB curing, a low oxygen atmosphere must be ensured to avoid surface inhibition.

Lower gloss coatings can be produced using standard matting agents. Care should be taken with respect to sedimentation which may cause the coating to gel prematurely.

TYPICAL PHYSICAL PROPERTIES

Acid number, mg KOH/g	0.2
Appearance	Clear to hazy
Colour, Pt-Co scale ⁽¹⁾	200
Density, g/ml at 20°C	1.14
Flash point, °C	>100
Functionality	3
Hydroxyl content, %	0.1
NCO, %	≤0.08
Viscosity, 23°C, cP/mPa·s	8000

TYPICAL CURED PROPERTIES

Tensile strength, psi (MPa)	3190 (22)
Elongation at break, %	17
Tg, °C	30

STORAGE AND HANDLING

Before using EBECRYL 4740, consult the Safety Data Sheet for additional information on safety and handling procedures, and recommended personal protective equipment.

The maximum recommended storage temperature for EBECRYL 4740 is 4°C to 40°C (39°F to 104°F). Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. Prevent inadvertent contact with peroxides and other radical initiators and contact with copper, copper alloys, carbon steel, iron and rust. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container.

EBECRYL 4740 can become hazy upon storage. This haze is reversible by stirring and/or oven heating to a maximum of 60 °C.

PRECAUTIONS

Avoid contact with eyes and skin. Direct contact with this material may cause moderate eye and skin irritation. Use with adequate ventilation. Wash thoroughly after handling. Keep container tightly closed.

(1) Product of Allnex

(2) Also referred to as APHA/Hazen colour

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

TRADEMARK NOTICE: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.