

# CYMEL<sup>®</sup> MB-94 resin

## PRODUCT DESCRIPTION

CYMEL MB-94 resin is an n-butylated melamine crosslinker with a high degree of alkylation and very low free formaldehyde. CYMEL MB-94 resin is designed for use in combination with urea resins for acid curing wood finishes to improve chemical resistance and cold check properties while maintaining fast drying properties.

## BENEFITS

- Fast cure
- Excellent compatibility
- Excellent chemical resistance properties
- Very low free formaldehyde

## APPLICATION AREAS

- Industrial wood finishes

## PHYSICAL PROPERTIES

| Property            | Range            | Method            |
|---------------------|------------------|-------------------|
| Appearance          | Clear Liquid     | Visual            |
| Non-volatile by wt. | 94-97%           | Foil, 45 min/45°C |
| Viscosity, 25°C     | Y-Z <sub>1</sub> | Gardner-Holdt     |
| Free formaldehyde   | < 0.1%           | Sulfite           |
| Color, Gardner      | < 1              |                   |

## SOLUBILITY

|                        |           |
|------------------------|-----------|
| Alcohols               | Complete  |
| Esters                 | Complete  |
| Ketones                | Complete  |
| Aromatic hydrocarbons  | Complete  |
| Aliphatic hydrocarbons | Complete  |
| Water                  | Insoluble |

## COMPATIBILITY

|                            |           |
|----------------------------|-----------|
| Acrylic resins             | Good      |
| Alkyd resins               | Very good |
| Polyester resins           | Good      |
| Epoxy resins               | Good      |
| Nitrocellulose             | Fair      |
| Cellulose acetate butyrate | Good      |
| Polyvinyl butyrate         | Good      |

## BACKBONE POLYMER SELECTION

CYMEL MB-94 resin is a very effective crosslinking agent for backbone polymer resins containing hydroxyl functional groups, such as alkyd, polyester or acrylic resins. The optimum level of CYMEL MB-94 resin in an acid curing wood coating formulation should be in the range of 25-35% on total resin solids if used as the sole crosslinker. Loadings of 5-10% on total resin solids is recommended when used in combination with a urea resin.

## CATALYSIS

CYMEL MB-94 resin responds best to sulfonic acid catalysts, like CYCAT<sup>®</sup> 4040 catalyst. Generally, 6-10% CYCAT 4040 catalyst on total resin solids of the formulation is sufficient to obtain fast drying behavior at room temperature.

## POT LIFE

To extend catalyzed pot life of the formulation, addition of primary alcohols, such as n-butanol and ethanol, is required at concentrations of 10-25% on total resin solids. Faster evaporating alcohols will improve speed of dry.

## STORAGE STABILITY

CYMEL MB-94 resin has a shelf life of 4 years from date of manufacture when stored at temperatures between 5°C and 30°C. Although low temperatures are not detrimental to stability, the viscosity of the product will increase making the resin more difficult to pump or pour. Product viscosity can be returned to normal by gentle re-warming, however, care should be taken to avoid excessive localized heating as this can cause an irreversible increase in viscosity.

---

• Worldwide Contact Info: [www.allnex.com](http://www.allnex.com) •

---

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with the ®, ™ or \* are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.

March 2015