

EBECRYL® 4220

Aliphatic Urethane Acrylate

March 2017



INTRODUCTION

EBECRYL 4220 is an aliphatic urethane acrylate diluted 25% in tripropyleneglycol diacrylate (TPGDA)⁽¹⁾. EBECRYL 4220 produces tough coatings that resist yellowing.

PERFORMANCE HIGHLIGHTS

UV/EB cured coatings based on EBECRYL 4220 are characterized by the following performance properties:

- Toughness
- Low yellowing

The actual properties of UV/EB energy cured products also depend on the selection of other formulation components such as reactive diluents, additives and photoinitiators.

SUGGESTED APPLICATIONS

EBECRYL 4220 is designed for use in the formulation of UV/EB energy curable coatings for application by roller coating, spraying and curtain coating on wood, cork, furniture, paper, parquet, plastics and film.

FORMULATING

Coatings can be adjusted to appropriate viscosity for the application with additional TPGDA or the addition of other standard reactive diluents such as 1,6-hexanediol diacrylate (HDDA)⁽¹⁾, isobornyl acrylate (IBOA)⁽¹⁾, and trimethylolpropane triacrylate (TMPTA)⁽¹⁾ or solvents such as butyl acetate.

EBECRYL 4220 is compatible with most acrylate monomers and oligomers. Because of the many potential combinations with reactive diluents and solvents, compatibility must be tested in each individual case.

UV curing of coatings formulated with EBECRYL 4220 requires the addition of standard commercial photoinitiators. Typical levels are 4-6%, though this may vary to meet the reactivity requirements of the application. In the case of EB curing, a low oxygen atmosphere must be ensured to avoid surface inhibition.

Lower gloss coatings can be produced using standard matting agents. Care should be taken with respect to sedimentation which may cause the coating to gel prematurely.

SPECIFICATIONS

	VALUE
Color, Pt-Co scale ⁽²⁾ , max.	150

TYPICAL PHYSICAL PROPERTIES

Acid value, mg KOH/g	1
Density, g/ml at 20°C	1.13
Flash point, °C	>100
Hydroxyl content, %	1
Viscosity, 23°C, cP/mPa·s	26000

PRECAUTIONS

Before using EBECRYL 4220, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

See the SDS for the recommended storage temperature range for EBECRYL 4220.

Please refer to the allnex Guide to Safety and Handling of Acrylate Oligomers and Monomers for additional information on the safe handling of acrylates.

(1) Product of allnex

(2) Also referred to as APHA/Hazen color

www.allnex.com

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.