

# EBECRYL<sup>®</sup> 8808

## Aliphatic Urethane Diacrylate

### INTRODUCTION

EBECRYL 8808 is an undiluted aliphatic urethane diacrylate. Since the oligomer is undiluted, more formulating latitude is possible. Films of EBECRYL 8808 cured by ultraviolet light (UV) or electron beam (EB) exhibit excellent exterior durability, toughness, and resistance to yellowing.

### PERFORMANCE HIGHLIGHTS

EBECRYL 8808 is characterized by:

- Light color
- No diluting monomers

UV/EB cured products containing EBECRYL 8808 are characterized by the following performance properties:

- Excellent exterior durability
- Excellent toughness
- Non-yellowing

The actual properties of UV/EB cured products also depend on the selection of other formulation components such as reactive diluents, additives and photoinitiators.

### SUGGESTED APPLICATIONS

Formulated UV/EB curable products containing EBECRYL 8808 may be applied via direct or reverse roll, offset gravure, metering rod, slot die, knife over roll, air knife, curtain, immersion and spin coating methods, as well as screen printing.

EBECRYL 8808 is recommended for use in:

- Screen inks and coatings on various substrates
- Non-yellowing, exterior durable coatings
- Coatings for wood and plastics

(1) Test methods are available upon request.

(2) UV cured 125  $\mu$  thick films.

### SPECIFICATIONS<sup>(1)</sup>

### VALUE

Appearance	Clear to slightly hazy liquid
------------	-------------------------------

### TYPICAL PROPERTIES

Color, Gardner scale	$\leq 2$
NCO %	$\leq 0.2$
Viscosity, 60°C, cP/mPa·s	12000-22000

### TYPICAL PHYSICAL PROPERTIES


Density, g/ml at 25°C	1.18
Functionality, theoretical	2
Oligomer, % by weight	100

### TYPICAL CURED PROPERTIES<sup>(2)</sup>

Tensile strength, psi (MPa)	5250 (36)
Elongation at break, %	63
Young's modulus, psi	50650 (349)
Glass transition temperature, °C	58

### GRAPH I

#### EBECRYL 8808 - VISCOSITY REDUCTION WITH REACTIVE DILUENT




## VISCOSITY REDUCTION

Graph I shows the viscosity reduction of EBECRYL 8808 with 1,6-hexanediol diacrylate (HDDA)<sup>(1)</sup>, isobornyl acrylate (IBOA)<sup>(1)</sup>, trimethylolpropane triacrylate (TMPTA)<sup>(1)</sup>, tripropylene glycol diacrylate (TPGDA)<sup>(1)</sup> and 2-phenoxyethyl acrylate (EBECRYL 114)<sup>(1)</sup>. Although viscosity reduction can be achieved with non-reactive solvents, reactive diluents are preferred because they are essentially 100 percent converted during UV/EB exposure to form a part of the coating or ink, thus reducing solvent emissions. The specific reactive diluents used will influence performance properties such as hardness and flexibility.

Graph II illustrates the change in viscosity of EBECRYL 8808 with increasing temperature.

## GRAPH II

### EBECRYL 8808 - VISCOSITY VS. TEMPERATURE



(1) Product of Allnex

## STORAGE AND HANDLING

Before using EBECRYL 8808, consult the **Safety Data Sheet** for additional information on safety and handling procedures, and recommended personal protective equipment.

The recommended storage temperature range for EBECRYL 8808 is 4°C to 40°C (39°F to 104°F). Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container.

## PRECAUTIONS

Avoid contact with eyes and skin. Direct contact with this material may cause moderate eye and skin irritation. Contact with skin may cause a cross-allergic reaction in persons already sensitized to acrylate materials. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

Please refer to the **Guide to Safety, Health and Handling of Acrylate Oligomers and Monomers** for additional information on the safe handling of acrylates .

• Worldwide Contact Info: [www.allnex.com](http://www.allnex.com) •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All rights reserved.

TRADEMARK NOTICE: Trademarks indicated with the ®, ™ or \* are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.

EBECRYL 8808 - TDS 9/11/2013