



Baerolub FTA SMS - US

Description Relatively high bulk density, free flowing flakes

Properties	<u>Test</u>	<u>Specification</u>
	Acid Value (mg KOH/g)	200-207
	Saponification Value (mg KOH/g)	201-208
	Iodine Value	1 max.
	Color (transmittance @ 440 nm)	85 min.
	Titer (congealing temperature, °C)	57-61 °C
	Unsaponifiable matter (%)	1.0 max.
	Chick Edema Free	Certified
	Bulk Density	Report lb/ft ³

Features Baerolub FTA SMS - US is produced from a high quality fatty acid for use as a lubricant for the extrusion of transparent PVC food film and other polymer applications requiring a low dusting, free-flowing lubricant and processing aid.

Performance Baerolub FTA SMS - US is a very effective external lubricant and internal lubricant supplement for the processing of flexible and rigid PVC and certain other polymer applications.

High apparent density and relatively large average particle size helps minimize dust exposure and housekeeping problems in the workplace.

The density and free-flowing nature of the flaked form prevents problems with bridging and caking and facilitates accurate dosing in virtually any type of bulk handling or conveying and automated weighing and metering systems.

Quality Control A modern, state-of-the-art plant process with strict control ensures consistent quality in chemical and mechanical properties.

Regulatory Meets FDA requirements under CFR21 for indirect food contact applications under the following citations: 175.105, 175.320, 176.170, 176.200, 177.1200, 177.2260, 178.3570 and 178.3910.

Packaging Bulk packaging in supersacks and palletized Kraft bags are available.

Storage Storage in dry areas at normal ambient temperatures is recommended. Open containers of unused product should be firmly closed for storage.

TDS-Baerolub FTA SMS - US 120913

NOTICE: Although the information and recommendations contained in this document (hereinafter "Information") are presented in good faith and believed to be correct at the date of their publication, BAERLOCHER makes no representations or warranties as to the completeness or accuracy of Information.

Information is supplied upon the condition that the persons or entities receiving same will make their own determination as to its suitability for their purposes prior to their use. In no event, will BAERLOCHER be responsible or liable for any loss of profits, lost goodwill, direct, special, indirect, incidental, or consequential damages of any nature whatsoever, including without limitation lost revenue, resulting from the use of or reliance upon Information or the product to which Information refers.

Nothing contained in this disclaimer is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent or intellectual property right, and BAERLOCHER makes no representation or warranty, express or implied, that the use thereof will not infringe any patent or intellectual property rights.

No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which Information refers.