

CYMEL® 304 resin

PRODUCT DESCRIPTION

CYMEL 304 resin is a specially alkylated, high solids melamine crosslinking agent designed specifically for industrial wood coating applications. Systems formulated with CYMEL 304 resin exhibit excellent catalyzed stability and films develop excellent early hardness, resistance properties, appearance and cold check resistance. It has very low free formaldehyde and low evolved formaldehyde on cure relative to conventional urea-based formulas.

BENEFITS

- Fast cure response in both ambient and forced cure applications
- Extended catalyzed coating stability
- Very low free formaldehyde

APPLICATION AREAS

- * Industrial wood coatings

PHYSICAL PROPERTIES

| Property | Range | Method |
|---------------------|-------------------|-------------------|
| Appearance | Clear Liquid | Visual |
| Non-volatile by wt. | > 98% | Foil, 45 min/45°C |
| Viscosity, 25°C | 4000 – 9000 mPa-s | Dynamic Viscosity |
| Free formaldehyde | ≤ 0.1% | Sulfite Method |
| Color, APHA | < 70 | ISO 6271 |

SOLUBILITY

| | |
|-----------------------|-----------|
| Alcohols | Complete |
| Esters | Complete |
| Ketones | Complete |
| Aromatic hydrocarbons | Complete |
| Water | Insoluble |

COMPATIBILITY

| | |
|------------------|-----------|
| Acrylic resins | Very good |
| Alkyd resins | Very good |
| Polyester resins | Very good |

BACKBONE POLYMER SELECTION

CYMEL 304 has excellent compatibility with a wide variety of polyols, such as alkyd, acrylic, and polyester resins. Polyols with primary hydroxyl functionality are preferred for fast cure at ambient conditions. The effective equivalent weight of CYMEL 304 resin is approximately 150, however, its optimum loading should be determined experimentally for each formulation with consideration of the performance properties to be optimized.

CATALYSIS

CYMEL 304 resin requires the addition of a sulfonic acid catalyst, such as CYCAT® 4040 catalyst, at levels of 6-10% on total resin solids in order to obtain effective cure for both ambient and heat cured applications. For pre-catalyzed urea-rich systems, 2.0% PAP based on weight of total binder solids is recommended.

FORMULATION STABILITY

The stability of formulated systems containing CYMEL 304 resin can be enhanced by the addition of primary alcohols, such as methanol, ethanol, and butanol. Higher concentrations will improve catalyzed pot life. Faster evaporating alcohols will improve speed of dry.

STORAGE STABILITY

CYMEL 304 resin has a shelf life of 5 years from the date of manufacture when stored at temperatures between 5°C and 30°C. Although lower temperatures are not detrimental to stability, its viscosity will increase, possibly making the resin difficult to pump or pour. The viscosity will reduce again on warming, but care should be taken to avoid excessive local heat, as this can cause an irreversible increase in viscosity.

CYMEL 304 resin has a shelf life of 60 months from date of manufacture when stored at temperatures between 5°C and 30°C

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.