

VANCRYL® 450

Colloidal Dispersion

June 2017



INTRODUCTION

VANCRYL 450 is a high solids colloidal dispersion that can be neutralized with ammonia or other alkaline materials to provide an outstanding vehicle for corrugated printing ink applications. This product, at 40% solids, reduces the cost in ink systems based on pre-neutralized colloidal acrylics.

VANCRYL 450 exhibits excellent black pigment grinding, and high drink in corrugated systems. This polymer, when neutralized with ammonia at 10% solids in water, has a viscosity of 150 cP, or about 40 seconds on a # 2 Zahn cup. It provides excellent transfer and printing at this low, economical solids level.

Neutralization can be easily accomplished by a simple mixing of 100 parts polymer wet, 95 parts water, and 5 parts ammonia. This mixture produces a 20% solids colloidal emulsion with a viscosity of 6000 to 9000 cP. It can be used in black pigment dispersions as well as color letdowns for corrugated inks.

This product is also an effective thickener for other formulations based on acrylic and styrenated acrylic polymers.

KEY PERFORMANCE PROPERTIES

- Higher jetness black dispersions
- Economy of high drink, low solids
- Excellent pigment compatibility
- Ease of neutralization
- Very low VOC content

TYPICAL PROPERTIES

	VALUE
Acid number, mg KOH/g	136
Density, lbs/gal	8.70
Flashpoint	Non-combustible
Grit rating, ppm	<25
Molecular weight, M_w	420000
Non-volatile matter, %	40
pH	5.8
Tg, °C	40
Tmff, °C	<0
Viscosity, at 25°C, cP	30
VOC, wt. %	<0.25

www.allnex.com

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.