

# CYMEL<sup>®</sup> U-227-8 resin

## PRODUCT DESCRIPTION

CYMEL U-227-8 resin is a general purpose n-butylated urea resin that combines fast curing speed with excellent enamel stability in pigmented systems. It is compatible with low and medium molecular weight epoxy resins and is recommended for use in epoxy/urea metal primers, metal decorating, and drum and dipping enamels. CYMEL U-227-8 resin is also recommended as a pigment grinding vehicle. It is supplied in a mixture of n-butanol and xylene.

## BENEFITS

- Very fast reaction speed
- Adhesion to metal substrates
- High flexibility

## APPLICATION AREAS

- General industrial bake finishes
- Primer formulations
- Dipping enamels

## PHYSICAL PROPERTIES

Property	Range	Method
Appearance	Clear Liquid	Visual
Non-volatile by wt.	52 ± 3%	Pan, 2 hrs/105°C
Viscosity, 23°C	1700-4500 mPa-s	Dynamic Viscosity
Viscosity, 25°C	X - Z <sub>1</sub>	Gardner-Holdt
Free formaldehyde	≤ 1.5%	Sulfite Method
Color, APHA	< 50	ISO 6271

## SOLUBILITY

Alcohols	Complete
Esters	Complete
Ketones	Complete
Aromatic hydrocarbons	Complete
Aliphatic hydrocarbons	Partial
Water	Insoluble

## COMPATIBILITY

Acrylic resins	Medium
Alkyd resins	Good
Epoxy resins	Good
Polyester resins	Good

## BACKBONE POLYMER SELECTION

CYMEL U-227-8 resin contains a combination of butoxymethyl and methylol functionalities, making it a very effective crosslinking agent for backbone polymers containing hydroxyl, carboxyl, and amide functionality. In addition to entering into crosslinking reactions, CYMEL U-227-8 resin also has a tendency toward self-condensation. Therefore, its practical equivalent weight, on a solids basis, is in the range of 200-280. Increasing the level of CYMEL U-227-8 resin in a coating formulation will generally increase the hardness and chemical resistance of the cured film, although higher levels may also increase brittleness. The optimum level in a particular formulation should always be determined experimentally.

## CATALYSIS

As with other urea-formaldehyde resins, CYMEL U-227-8 resin may not require the addition of an acid catalyst to the formulation in order to obtain effective cure. In many instances, the acidity of other formulation components is sufficient to catalyze reaction. If catalyst addition is required, then 0.5-1.0% of either CYCAT<sup>®</sup> 4040 catalyst or CYCAT 296-6 catalyst, based on weight of total binder solids, is recommended for normal bake schedules (15-20 minutes at 120-150°C).

## FORMULATION STABILITY

The stability of formulated systems containing CYMEL U-227-8 resin can be enhanced by the addition of alcohols, amines or a combination of these. Low molecular weight primary alcohols such as ethanol and n-butanol are most effective. Recommended amines are TEA, DMEA or 2-AMP at a concentration of 0.5-1.0% on total binder solids.

## STORAGE STABILITY

CYMEL U-227-8 resin has a shelf life of 4 years from date of manufacture when stored at temperatures between 5°C and 30°C. Although low temperatures are not detrimental to stability, the viscosity of the product will increase making the resin more difficult to pump or pour. Product viscosity can be returned to normal by gentle re-warming, however, care should be taken to avoid excessive localized heating as this can cause an irreversible increase in viscosity.

---

• Worldwide Contact Info: [www.allnex.com](http://www.allnex.com) •

---

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with the ®, ™ or \* are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.