

# EBECRYL® 113

Aliphatic Monofunctional Acrylate

March 2017



## INTRODUCTION

EBECRYL 113 is a low odor monofunctional acrylated aliphatic epoxy that can be used as a reactive diluent in ultraviolet light (UV) or electron beam (EB) curing formulations. EBECRYL 113 is a good diluent for a variety of acrylated oligomers. In formulations, it can lower T<sub>g</sub>, increase flexibility and improve adhesion to plastics.

## PERFORMANCE HIGHLIGHTS

EBECRYL 113 is characterized by:

- Low odor
- Low viscosity
- Efficient reduction of oligomer viscosity
- Good pigment wetting

UV/EB cured products based on EBECRYL 113 are characterized by the following performance properties:

- Good reactivity
- Improved flexibility
- Decreased T<sub>g</sub>
- Improved water resistance
- Reduced shrinkage, improved adhesion

The actual properties of UV/EB cured products also depend on the selection of the other formulation components such as oligomers, additives and photoinitiators.

## SUGGESTED APPLICATIONS

EBECRYL 113 is recommended as a reactive diluent for:

- Screen inks and varnishes
- Coatings for paper and plastic
- Water resistant coatings
- Flexible coatings
- Coatings and inks with adhesion to plastics such as polyethylene and plasticized PVC
- Wood sealers and topcoats

## SPECIFICATIONS

	VALUE
Acid value, mg KOH/g, max.	1.0
Acrylic acid content, ppm, max.	2000
Appearance	Clear liquid
Color, Gardner scale, max.	3.0
Epoxy content, %, max.	0.1
Viscosity, 25°C, cP/mPa·s	90-150

## TYPICAL PHYSICAL PROPERTIES

Density, g/ml at 25°C	0.97
Flash point, Setflash, °C	>100
Functionality, theoretical	1
Surface tension, dynes/cm	31.9

## PRECAUTIONS

Before using EBECRYL 113, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

## STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

See the SDS for the recommended storage temperature range for EBECRYL 113.

Please refer to the allnex Guide to Safety and Handling of Acrylate Oligomers and Monomers for additional information on the safe handling of acrylates.

[www.allnex.com](http://www.allnex.com)

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or \* as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.