

ZHEJIANG FENGHONG NEW MATERIAL CO. ,LTD. <u>Http://www.zjfenghong.com</u> E-mail: <u>Bentonite@zjfenghong.com</u> Tel: +86-571-63806068/63711876 Fax:+86-571-63751569/63806098 Add: Tangpu Developing Zone, Anji County, Zhejiang Province, China. P.C.313300

Version:Mar.2020

## ZHEJIANG FENGHONG NEW MATERIAL CO., LTD.

## www.zjfenghong.com



**BS-1C-A25** 

# **Rheology Modifier**

### **GENERAL INFORMATION**

BS-1C-A25 is a new composite clay suitable for using in a broad range of coatings systems including epoxies and unsaturated polyesters. BS-1C-A25 imparts excellent sag resistance, thixotropy and suspension property.

## ADVANTAGES

 $\gtrsim$  Easy to incorporate-no need for chemical activator.

- $rac{1}{2}$  Particularly suitable for solventless epoxy system&high polarity system
- ☆Dust free addition
- $\Rightarrow$ Strong pseudoplasticity

PHYSICAL PROPERTES	RECOMMENDED USE
Composition: Amine-treated clay	<ul> <li>Construction paint (sewing agent)</li> </ul>
Color/Form:Pale yellow free flowing powder	Anti-Corrosion paint     (solventless epoxy)
Moisture: < 10.0%	<ul> <li>Industrial paint(UPR)</li> </ul>
Fineness : 98% Min thru 325 mesh	Hot melt marking paint
	Adhesives, caulks and sealants
	Cleaning agent

## INCORPORATIONS

BS-1C-A25 belongs to the type of unconventional organoclay group. Being self-activated organoclay, it dose not required heat or chemical activator to reach the proper activation. BS-1C-A25 can be incorporated directly into the resin. (Note:Do not add immediately after the addition of wetting&dispersing agent; Suggest to add immediately after big amount of pigment&filler. Only when the solid content is high, it can be added before filler for better wetting.)

In unsaturated and aromatic systems, preparation of a 10% pregel in styrene is



ZHEJIANG FENGHONG NEW MATERIAL CO., LTD. <u>Http://www.zjfenghong.com</u> E-mail: <u>Bentonite@zjfenghong.com</u> Tel:+86-571-63806068/63711876 Fax:+86-571-63751569/63806098 Add: Tangpu Developing Zone, Anji County, Zhejiang Province, China. P.C.313300

recommended to achieve optimal efficiency. Polar activator(5-10% by wt.of clay) can be added when it is mixed with incompatible solvent.

#### **RECOMMENDED LEVELS**

BS-1C-A25 is typically used at levels of 0.5% - 3% by weight of the system, depending upon the degree of thickening or other properties desired. Laboratory testing is recommended to determine optimal level.

#### **HEALTH AND SAFETY DATA**

Before handling this material, read the corresponding Safety Data Sheet (SDS) for safety, health and environmental data.

#### SHELF LIFE

BS-1C-A25 has a shelf life of at least two years from date of manufacture. Store in a cool dry place.

#### CERTIFICATIONS

ISO 9001 Quality System, ISO 14001 Environmental Management System, ISO 18001 Safety System

#### MANUFACTURER: ZHEJIANG FENGHONG NEW MATERIAL CO., LTD.

#### www.zjfenghong.com

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchant ability and fitness for use. Purchases will be subject to a separate agreement which will not incorporate this document.