

## VPS WS 602

**Aqueous emulsion for the water repellent treatment of mineral porous materials. Essentially VOC free.**

### Technical Data

Properties and test methods	Value	Unit	Method
Density (20 °C)	approx. 1,017	g/cm <sup>3</sup>	DIN 51757
Appearance	white liquid	-	-
Flash point	> 90	°C	EN 22719
Viscosity (20 °C)	approx. 20	mPa.s	DIN 53015
Active ingredient	50	%	-
pH (20°C)	6,5 - 8,5	-	-

### Registration

#### VPS WS 602

EINECS/ELINCS (EU):	Yes
AICS (Australia):	No
DSL/NDSL (Canada):	*
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	*
ENCS (Japan):	Yes
ECL (South Korea):	Yes
TCSI (Taiwan)	Yes
*= Information upon request	

Aqueous emulsion for the water repellent treatment of mineral porous materials. Essentially VOC free.

### Safety and Handling

Before considering the use of Protectosil® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website [www.protectosil.com](http://www.protectosil.com) or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

### Packaging and Storage

VPS WS 602 is supplied in 25 l PE-containers, 200 l steel drums with PE-inliner and 1.000 l containers. VPS WS 602 is not frost resistant and should not be stored at temperatures below 3 °C. Only demineralized water should be used for dilutions. VPS WS 602 should be stored at temperatures between 3 °C and 40 °C. VPS WS 602 has a shelf life of 12 months if properly stored in originally sealed containers.

## Properties and Use

### VPS WS 602

- is suited for the water repellent impregnation of porous mineral substrates
- does not form sticky silicone films
- shows very good penetration on absorbent mineral materials
- gives water vapor permeable, colorless protection
- reduces significantly the uptake of water
- repels water soluble pollutants
- effective on micro cracks of up to 0.3 mm
- can be diluted with water
- is very efficient on mineral rendering, sand-lime brickwork, hard-baked brickwork, roofing tiles

We recommend using a minimum concentration of 10% of the active ingredient in water. This corresponds to a dilution with water (preferable demineralized water) of 1:4. VPS WS 602 is not recommended to be applied undiluted. Minimum dilution rate should be 1:1.

The concentration to be used and the exact amount to be applied are depending on the absorbance of the substrate.

The substrates to be treated should be dry and clean. Acceptable surface cleaning methods include sandblasting and water blasting.

During application outside temperatures and surface temperatures should be between 5 °C and 40 °C. VPS WS 602 should not be applied during strong wind or rain.

VPS WS 602 should be applied by wet-on-wet flow coating to the saturation point. The solution should be applied in 2 - 3 coats without drying between the coats. On vertical surfaces the solution should run down in the form of a clearly visible descending wet curtain. This is achieved by allowing the solution to flow against the surface of the building material without pressure. Most liquid delivery devices e.g. airless pumping equipment are suitable. The material should not be atomized or applied with a brush.

The water repellent effect of VPS WS 602 can develop within minutes or require up to several days depending on the substrate and weather conditions. Therefore, the impregnation should be applied continuously and without a break to avoid overlapping.

Non-absorbent substrates such as window frames, window sills, plastic fittings, window glass, etc., should be covered before application. Surfaces which accidentally come into contact with VPS WS 602 can be cleaned with alcohol (spirit) or aqueous soap solution. Cleaning should be carried out as quickly as possible (within a few hours), otherwise formation of a silicone resin film can make cleaning more difficult. Silicone resin films are best removed using ethanol (or spirit). Plant life should be protected from overspray.

VPS WS 602 reacts with the interfaces in pores and capillaries of the mineral surface and forms invisible, waterrepellent interfacial compounds. To determine the exact amount to be applied and to check whether previous or following treatments are compatible with the VPS WS 602 treatment it is recommended to do a small test patch first.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Europe / Middle-East / Africa / Row**

**Evonik Resource Efficiency GmbH**

Business Line Silanes  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 13636  
FAX +49 6181 59 713 915  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik (SEA) Pte. Ltd.**

Business Line Silanes  
3 Internatioanl Business Park  
#07-18, Nordic European Centre  
Singapore 609927  
PHONE +65 6809 6899  
FAX +65 6809 6699  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik Taiwan Ltd.**

Business Line Silanes  
Artist Construction Bldg  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan 10596  
PHONE +886 227 17 1242  
FAX +886 227 17 2106  
protectosil@evonik.com  
www.protectosil.com

**North America**

**Evonik Corporation**

Business Line Silanes  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE (TOLL FREE) +1 800 828 0919  
FAX +1 973 929 8503  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik (Shanghai) Co. Ltd.**

Business Line Silanes  
55, Chungdong Road  
Shanghai 201108  
P.R. China  
PHONE +86 21 6119 1660  
FAX +86 21 6119 1075  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik Japan Co. Ltd**

Business Line Silanes  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7446  
FAX +81 353 23 7397  
protectosil@evonik.com  
www.protectosil.com

**Latin America**

**Evonik Brasil Ltda.**

Business Line Silanes  
Alameda Campinas, 579  
01404-000 São Paulo-SP  
Brazil  
PHONE +55 11 3146 4123  
FAX +55 11 3146 4148  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik Korea Ltd.**

Business Line Silanes  
94, Galsan 1-dong  
Bupyeong-gu  
Incheon, 403-081, Korea  
PHONE +82 2320 4778  
FAX +82 2783 2520  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik India Pvt. Ltd.**

Business Line Silanes  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
protectosil@evonik.com  
www.protectosil.com