

CYMEL[®] NF 2000A resin

December 2019



The Coating Resins Company

PRODUCT DESCRIPTION

CYMEL NF 2000A resin is a unique trifunctional melamine-based crosslinker containing reactive carbamate functionality supplied in n-butanol. It can be used to crosslink hydroxy- and epoxy-containing polymers to give highly durable, acid-resistant films that exhibit a favorable balance of hardness and flexibility. An important feature of CYMEL NF 2000A resin is that it does not contain or emit formaldehyde on cure. It can be employed as the sole crosslinker in a coating or ink formulation, or it may be used at lower levels in combination with other crosslinkers, such as amino resins or isocyanates, in order to obtain a balance of properties. CYMEL NF 2000A resin is recommended for high quality durable finishes such as automotive topcoats, exterior can varnishes, and coil coatings.

BENEFITS

- Excellent environmental etch resistance
- Excellent exterior durability
- Non-formaldehyde chemistry
- Non-isocyanate chemistry
- Cure compatibility with other crosslinkers
- Low equivalent weight / high efficiency
- Low human toxicity

APPLICATION AREAS

- Automotive topcoats
- Coil coatings
- Exterior can coatings
- Solvent-borne and waterborne coatings

PHYSICAL PROPERTIES

Property	Range	Method
Appearance ¹	Clear to slight haze	ASTM E284
Non-volatile	48 - 52%	DIN EN ISO 3251 (Pan, 2 hr/105°C)
Viscosity, 23°C	10 - 50 mPa·s	DIN EN ISO 3219
Color, APHA	≤ 50	DIN EN ISO 6271
pH	3.0 - 6.0	DIN 55659-1

¹Product may become hazy during storage as the active ingredient is near its solubility limit in solution. The haze development has no impact on performance of the product or the clarity of resulting films.

TYPICAL PROPERTIES (NOT CONTINUALLY DETERMINED)

Property	Range	Method
Sodium Content	< 100 ppm	ICP
Turbidity ²	< 2.5 NTU	DIN EN 27027

²At time of manufacture


COMPATIBILITY

Acrylic resins	Good
Alkyd resins	Very good
Polyester resins	Very good
Epoxy resins	Good

SOLUBILITY

Alcohols	Soluble
Esters	Soluble
Glycol ethers	Soluble
Aromatic hydrocarbons	Soluble
Water	Insoluble

Tris(Alkoxy-carbonylamino) Triazine




R = CH₃, n-C₄H₉

REACTIVITY & BACKBONE POLYMER SELECTION

CYMEL NF 2000A resin contains a combination of butyl and methyl carbamate functionality which enables it to crosslink backbone polymers containing hydroxy, epoxy and carboxy functionality. Unlike conventional amino resins, CYMEL NF 2000A resin has very little tendency to self-react during cure, so its effective equivalent weight is in the range of 120-130. In formulations where it is employed as the sole crosslinker, the level of CYMEL NF 2000A resin is normally adjusted to provide a ratio of 1.0 - 1.1 equivalents of carbamate functionality per equivalent of backbone polymer functionality.


CYMEL NF 2000A resin reacts with hydroxy functional backbone resins at >125°C bake schedules to form urethane linkages. Cure can typically be accomplished without use of a catalyst to yield films that exhibit excellent hardness, chemical resistance, exterior durability and environmental etch resistance. Addition of low levels of acid catalyst (e.g. 0.5% dodecyl benzene sulfonic acid on binder solids) has been found to improve humidity resistance properties in some systems. Both catalyzed and uncatalyzed formulations show good 1K package stability at 23°C. CYMEL NF 2000A resin will react with carboxy functional backbone resins, but requires bake temperatures >150°C.



STORAGE STABILITY

CYMEL NF 2000A resin has a shelf life of 720 days from the date of manufacture when stored at temperatures below 32°C.

CYMEL NF 2000A resin reacts very efficiently with epoxy functional resins at ~125°C resulting in N-substituted carbamate and oxazolidone crosslinks. Films produced through this cure mechanism often show a favorable combination of environmental etch resistance and mar resistance properties. In most cases, a tertiary amine or quaternary ammonium catalyst such as 4-dimethylaminopyridine should be employed in the formulation. However, catalyzed pot life can be limited, making it necessary to treat these as two-component systems.



USE AS A CO-CROSSLINKING AGENT

A significant advantage of CYMEL NF 2000A resin is its cure compatibility with other thermoset chemistries. Since its cure response with hydroxy-functional resins is not appreciably inhibited by amines, acids, or metal catalysts, it can be used effectively as a co-crosslinking agent with other materials, such as traditional aminoplasts or isocyanates. Incorporation of low levels of CYMEL NF 2000A resin (e.g. 1-5 wt. % on total resin solids) into a conventional polyol/aminoplast coating formulation can significantly improve the exterior durability of the cured film.

USE IN WATERBORNE SYSTEMS

CYMEL NF 2000A resin can be used in water-reducible resins and with waterborne dispersions. Although it is water insoluble, it can be incorporated into a water-reducible system by blending with the backbone resin prior to amine neutralization. These systems can be cured at ~125°C to give clear, high gloss films with excellent resistance properties. When using the material in water-based systems it is recommended that a tertiary amine be utilized as the neutralizing agent for the system in order to avoid the possibility of degrading the CYMEL NF 2000A resin.

www.allnex.com

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex IP Sàrl or its directly or indirectly affiliated Allnex Group companies.