

# 3M™ Glass Bubbles S42XHS-OG-ES-1

## Introduction

3M™ Glass Bubbles S42XHS-OG-ES-1 are high-strength polymer additives made from a water-resistant and chemically-stable soda-lime borosilicate glass. 3M glass bubbles S42XHS-OG-ES-1 have been treated with a proprietary silane coupling agent for use in applications with unsaturated Polyesters, Acrylics, EVA and Polyolefins. These hollow glass microspheres can be used as a low density filler material ideal for liquid thermoset as well as thermoplastic and rubber parts created from molding, extrusion processes, and/or other vigorous processing equipment (e.g., Banbury mixers, etc.), offering improved processing over many conventional fillers.

3M glass bubbles S42XHS-OG-ES-1 may help to reduce weight, improve dimensional stability, reduce shrinkage and sink marks, and contribute to material and process cost savings. They may be ideal additive materials for applications in the automotive, heavy truck, aerospace, electrical, sports and leisure, electronics, appliance and durable goods industries, as well as in construction products such as polymer/wood composites and siding – helping not only to reduce part weight, but also to improve dimensional stability.

## Material Description (Not for specification purposes.)

Properties	3M™ Glass Bubbles S42XHS-OG-ES-1
Shape	Hollow spheres with thin walls
Composition	Soda-lime-borosilicate glass
Color, unaided eye	Off-white, powdery

## Typical Physical Properties (Not for specification purposes.)

Properties	3M™ Glass Bubbles S42XHS-OG-ES-1	Test Method
Isostatic crush strength	8,000 psi	3M QCM 14.1.8
True density	0.42 g/cc	3M QCM 14.24.1
Packing factor (bulk density to true particle density)	60%	–
% Bond	0.75% Min.	3M QCM19.19
Average diameter (microns)	25	3M QCM 193.0

## Formulating Information

**Flow properties:** 3M glass bubbles S42XHS-OG-ES-1 will remain free-flowing for at least one year from the date of shipment from 3M when stored in the original, unopened container in accordance with the recommended storage conditions. (See below for storage recommendations.)

**Glass bubble breakage:** Breakage may occur if the product is severely processed. To minimize breakage, minimize exposure to high shear processes and to point contact shear, such as inter-meshing gear pumps, 2-roll and 3-roll mills. When adding to an extrusion process, the material should be added down stream of the feed hopper via a side-stuffer or top feeder (similar to adding glass fiber).

## Product Storage, Handling and Safety

**Storage:** Ideal storage conditions include unopened cartons in a dry and temperature-controlled warehouse.

Extended exposure of 3M glass bubbles S42XHS-OG-ES-1 boxes to high humidity and/or conditions susceptible to condensation may result in some amount of “caking” of the glass bubbles. To minimize the potential for caking and thereby maximize storage life, the following suggestions are offered:

1. Carefully re-tie opened bags immediately after use.
2. If the polyethylene bag is punctured during shipping or handling, seal the hole as soon as possible or insert the contents into an undamaged bag.
3. During hot and/or humid months, store boxes in the driest, coolest space available.

If controlled storage conditions are unavailable, carry a minimum inventory and process on a first in/first out basis.

**Handling:** Due to the low weight and small particle size of 3M glass bubbles S42XHS-OG-ES-1, dusting may occur while handling and processing. To minimize the dusting potential during handling, consider the following:

- Do not open glass bubbles packages until ready to use.
- Upon opening, have an air siphon near the opening to pull away airborne particles. (Dust collection equipment may be required – check OSHA and other applicable regulations.)
- Remove glass bubbles with a suction “wand” (with slight positive pressure aeration) and transfer to a closed mixing tank inside fully contained piping. If a closed mixing tank is not available, use dust collection equipment as close as practical to the point of entry. Pneumatic conveyor systems have been used successfully to transport glass bubbles without dusting from shipping containers to batch mixing equipment. Equipment vendors should be consulted for recommendations.

- Static eliminators should be used to prevent static buildup.

**Safety:** For worker protection, please consider the following:

- Use safety glasses with side shields for eye protection.
- For respiratory protection, wear an appropriate NIOSH/MSHA approved respirator based on airborne concentration of contaminants and in accordance with OSHA regulations. (For additional information about personal protective equipment, refer to the product Material Safety Data Sheet.)
- Use with appropriate local exhaust ventilation/dust collection in the work area.

## Additional Information

3M™ Glass Bubbles are supported by global sales, technical and customer service resources, with fully-staffed technical service laboratories in the U.S., Europe, Japan, Latin America and Southeast Asia. Users benefit from 3M's broad technology base and continuing attention to product development, performance, safety and environmental issues.

For additional technical information on 3M glass bubbles in the United States, call 3M Advanced Materials Division, **800-367-8905**.

For other 3M global offices, and information on additional 3M products, visit our web site at: **[www.3M.com/engineeredadditives](http://www.3M.com/engineeredadditives)**.

**Warranty, Limited Remedy, and Disclaimer:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. User is solely responsible for evaluating third party intellectual property rights and for ensuring that user's use of 3M product does not violate any third party intellectual property rights. Unless a different warranty is specifically stated in the applicable product literature or packaging insert, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OF NON-INFRINGEMENT OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except where prohibited by law, 3M will not be liable for any loss or damages arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

**Technical Information:** Technical information, recommendations, and other statements contained in this document or provided by 3M personnel are based on tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

