

TEGO® Foamex 822

DESCRIPTION

TEGO® Foamex 822 is a compatible defoamer emulsion based on polyether siloxane technology. Good balance of compatibility and long term effectiveness.

KEY BENEFITS

- very good as combination partner with e.g. defoamer concentrates
- highly suitable for sensitive waterborne formulations
- suitable for clear formulations

APPLICATION RECOMMENDATION

Brush application/roller application



Airless spraying



Compressed air spraying



Flexo/gravure printing



Dip coating, flow coating, curtain coating



Flooring



SUITABILITY

waterborne	solventborne
●	●
2-pack 100%	radiation-curing
●	●
addition to the grinding stage	addition to the let-down stage
●	●

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Transportation coatings
- Parquet coatings
- Wood coatings
- Plastic coatings

TECHNICAL DATA

active matter content	20 %
appearance	white thixotropic liquid
chemical description	emulsion of a polyether siloxane copolymer, contains fumed silica
solvent	solvent-free

SOLUBILITY

For stability reasons emulsions may not be diluted by organic solvents.

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.1 - 1.0 %

PROCESSING INSTRUCTIONS

- Long term effectiveness of the product is dependent on the formulation and should be tested in individual formulations.
- Addition to the coating as supplied.
- Before use, mix briefly with low shear forces.

HANDLING & STORAGE

When stored in an original unopened packaging between +4 and +40 °C, the product has a shelf life of at least 12 months from the date of manufacture.

MSDS & REGULATORY INFORMATION



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Resource Efficiency GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com