



## VERSAL RED FGRD 01


 TiO<sub>2</sub> 1:1


 TiO<sub>2</sub> 1:10

### Characteristic

C. I.	Pigment Red 112
C. I. No.	12370
CAS No.	6535-46-2
Chemical Class	2-Naphthol

### Properties

Oil Absorption [ml/100 g]	57
Bulking Volume [l/kg]	6.9

### Fastness

Linseed Oil	3
White Spirite	4
DEHT	4
Xylene	2-3
Acetone	3
Butylacetate	3
Ethanol	3-4
Water	5
HCl 2.5%	5
NaOH 2.5%	5
Light - Full Shade	7-8
Light - 1/1	7
Light - 1/3	6-7
Weather - Full Shade	4-5
Weather - 1/1	4
Weather - 1/3	3
Overspray	3
Heat Resistance [°C]	C 180
Migration	

C - in Coatings

### Application Possibilities

Printing Inks - Nitrocellulose	●
Printing Inks - Water based	●
Printing Inks - Offset	○
Printing Inks - UV Curing	●
Paints - Decorative	●
Paints - Industrial	○
● main application	○ side application

### Other Informations

Shelf Life	48 months
------------	-----------

### Testing methods

#### Density

- determined by ČSN EN ISO 787-10: 1997 (67 0520) in  $\text{v g/cm}^3$

#### Bulking Volume

- denotes the volume of 1 kg of loosely poured pigment, expressed in litres

#### Oil Absorbtion

- determined by ČSN EN ISO 787-5: 1997 (67 0520) in ml/100 g pigment

#### Fastness to Solvents

- colouring of solvent after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one

#### Fastness to Reagents

- colouring of reagents after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one

#### Light Fastness - Xenotest

- determined by ČSN EN ISO 105-B02: 2000 (80 0147) and evaluated in 1/3 and 1/1 of standard depth and in full shade; determined according to blue scale, by it degree 1 denotes the lowest fastness, degree 8 the highest one

#### Weathering Fastness - Xenotest

- determined by ČSN EN ISO 105-B04: 1998 (80 0171) and evaluated in 1/3 and 1/1 of standard depth and in full shade; determined according to grey scale, by it degree 1 denotes the lowest fastness, degree 5 the highest one

#### Overspray Fastness

- assessment of bleeding into a white nitrocellulose combination lacquer for 60 min. at 70 °C against ISO grey scale; by it degree 1 denotes the lowest fastness, degree 5 the highest one

#### Heat Resistance

- the values quoted indicate up to what temperature the pigments do not significantly alter; these are guide values which can be influenced by the binder used and the period of exposure to high temperature

#### Migration Fastness

- assessment of bleeding into a white polyvinylchloride sheet for 24 h at 70 °C against ISO grey scale; by it degree 1 denotes the lowest fastness, degree 5 the highest one; no data means that the pigment is not recommended for dyeing of PVC

#### Fastness to plasticizers

- colouring of plasticizer (diethylhexylterephthalate) after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one