

## **TECHNICAL DATA SHEET**

<b>TDS</b>	276

Revision:	Date:	Page:
00	12/18/2019	1/1

# **BREUTEX H**

100% Elliottii Rosin obtained by distillation of crude qum / pine oleoresin collected from Pinus trees (live).

VERIFICATIONS			
Characteristics	UN	Specification / Tolerance	Method
Color Gardner (50% in Toluene)	-	Máx. 6	ML RB 001
Color US Standard	-	Máx. X	ML RB 001
Acid Number	Mg KOH/g	Mín. 165	ML RB 002
Softening Point (Ring and Ball)	°C	Mín. 76	ML RB 003
Solubility in Ethanol	-	Soluble	ML RB 002
*Saponification Number	Mg KOH/g	Mín. 175	ML RB 007
*Insoluble in Toluene	%	Máx. 0,02	ML RB 015

<sup>\*</sup>Sporadically tested properties for reference only.

#### **APPLICATIONS**

☑ Rosin Derivaties, depilatory wax etc.

#### **BENEFITS**

- Renewable source product;
- Improves adherence and transparency of glues and adhesives;
- Improves adherence and Good reactivity to preparation derivatives such as esters and reactions with maleic anhydride and fumaric acid;
- ☑ Improves astringency and hardness of saponified materials (soap).

PACKAGING				
Туре	Size	Shelf life		
Zinc Steel Drum	250 kg	18 months		
Cartons (solid)	25 kg	18 months		
Multiwall Kraft paper bags (solid)	25 kg	18 months		
Braided polypropylene bags	25 kg	6 months		
Cartons (flakes)	25 kg	6 months		
Multiwall Kraft paper bags (flakes)	25 kg	6 months		
DICCLAIMED				

### **DISCLAIMER**

To prevent accidents and impacts environmental, please check the product SDS.

We request our customers to test our products before using them on industrial scale. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. We do not assume any responsibility or warranty, expressed or implied, resulting from handling, usage and storage whether performed according to the instructions contained in this document, whether used alone or in combination with other products. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, either alone or in combination with other products.

Elaborated: Rafaela Silva	Revised: Antônio Vieira	Approved: Francisco Fernandez
---------------------------	-------------------------	-------------------------------