

SUKOREZ SU-210**Hydrogenated C5/Cyclic hydrocarbon resin**

23th/6/2005

SUKOREZ SU-210 is light color thermoplastic resin obtained from polymerizing of C5 / Cyclic and hydrogenation. The major usages are tackifier for hot melt adhesive(HMA), hot melt pressure sensitive adhesive(HMPSA) because of its good heat resistance and good compatibility with base polymers such as ethylene vinyl acetate(EVA), Styrene-Isoprene-Styrene block copolymer(SIS).

SPECIFICATIONS

Softening Point (Ring & Ball, °C)	107-114	ASTM E 28
Color (50% Toluene Solution, HAZEN)	Max.100	ASTM D 1209

TYPICAL PROPERTIES

Specific Gravity (20/20°C)	1.08	ASTM D 71
Softening Point (Ring & Ball, °C)	110	ASTM E 28
Color (50% Toluene Solution, HAZEN)	80	ASTM D 1209
Acid Value (KOHmg/g)	0.04	ASTM D 974
BRF, @160°C, cps	1,500	
BRF, @180°C, cps	340	
Molecular Weight (GPC, Mw)	530	G.P.C

Kolon Chemical Company and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

PACKAGING

SUKOREZ SU-210 is available both in big bags of 500kgs net weight and in multi-ply paper bags of 25kgs net weight.

STORAGE

Pelletized forms of resins may block or lump in hot weather climates or if stored near heat sources. Inside storage is recommended and keep at temperature not exceeding 30°C

REGULATORY STATUS

SUKOREZ SU-210 is in compliance with the requirements of the U.S FDA for following sections.

175.105	Adhesives
175.125	Pressure sensitive adhesives
175.300	Resinous and polymeric coatings
175.320	Resinous and polymeric coatings for poly olefin films
176.170	Components of paper and paperboard in contact with aqueous and fatty foods.
176.180	Components of paper and paperboard in contact with dry food
177.1210	Closures with sealing gaskets for food containers
177.1520	Olefin polymers
177.2600	Rubber articles intended for repeated use

 **KOLON CHEMICAL CO., LTD.**

HEAD OFFICE : 10TH FL., KOLON TOWER 1-23, BYULYANG-DONG GWACHEON-CITY KYUNGGI-DO, KOREA
TEL) 82-2-3677-6120 FAX) 82-2-3677-6191

YEOSU PLANT : 8-2BL, National Industrial Complex, Jungheung-Dong, YEOSU-CITY, Jeonnam, KOREA
TEL) 82-61-690-9860 FAX) 82-61-690-9899
